

Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs (Text with EEA relevance) (repealed)

[<sup>X1</sup>COMMISSION DIRECTIVE 2002/72/EC  
of 6 August 2002

relating to plastic materials and articles intended to come into contact with foodstuffs  
(Text with EEA relevance)] (repealed)

[<sup>X1</sup>THE COMMISSION OF THE EUROPEAN COMMUNITIES,

Having regard to the Treaty establishing the European Community,

Having regard to Council Directive 89/109/EEC of 21 December 1988 on the approximation of the laws of the Member States relating to materials and articles intended to come into contact with foodstuffs<sup>(1)</sup>, and in particular Article 3 thereof,

After consulting the Scientific Committee on Food,

Whereas:

- (1) Commission Directive 90/128/EEC of 23 February 1990 relating to plastic materials and articles intended to come into contact with foodstuffs<sup>(2)</sup>, as last amended by Directive 2002/17/EC<sup>(3)</sup>, has been frequently and substantially amended; for reasons of clarity and rationality, it should therefore be consolidated.
- (2) Article 2 of Directive 89/109/EEC lays down that materials and articles, in their finished state, must not transfer their constituents to foodstuffs in quantities which could endanger human health or bring about an unacceptable change in the composition of the foodstuffs.
- (3) In order to achieve this objective in the case of plastic materials and articles, a suitable instrument is a specific Directive within the meaning of Article 3 of Directive 89/109/EEC, the general provisions of which are also applicable to the case in question.
- (4) The scope of this Directive must coincide with that of Council Directive 82/711/EEC<sup>(4)</sup>.
- (5) Since the rules established in this Directive are not suitable for ion-exchange resins, these materials and articles will be covered by a subsequent specific Directive.
- (6) Silicones should be regarded as elastomeric materials rather than plastic materials and therefore should be excluded from the definition of plastic.
- (7) The establishment of a list of approved substances accompanied by a limit on overall migration and, where necessary, by other specific restrictions will be sufficient to achieve the objective laid down in Article 2 of Directive 89/109/EEC.
- (8) Besides the monomers and other starting substances fully evaluated and authorised at Community level, there are also monomers and starting substances evaluated and

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

authorised in at least one Member State which may continue to be used pending their evaluation by the Scientific Committee on Food and the decision on their inclusion in the Community list; this Directive will accordingly be extended in due course to the substances and sectors provisionally excluded.

- (9) The current list of additives is an incomplete list inasmuch as it does not contain all the substances which are currently accepted in one or more Member States; accordingly, these substances continue to be regulated by national laws pending a decision on inclusion in the Community list.
- (10) This Directive establishes specifications for only a few substances. The other substances, which may require specifications, therefore remain regulated in this respect by national laws pending a decision at Community level.
- (11) For certain additives the restrictions established in this Directive cannot yet be applied in all situations pending the collection and evaluation of all the data needed for a better estimation of the exposure of the consumer in some specific situations; therefore, these additives appear in a list other than that of the additives fully regulated at Community level.
- (12) Directive 82/711/EEC lays down the basic rules necessary for testing migration of the constituents of plastic materials and articles and Council Directive 85/572/EEC<sup>(5)</sup> establishes the list of simulants to be used in the migration tests.
- (13) The determination of a quantity of a substance in a finished material or article is simpler than the determination of its specific migration level. The verification of compliance through the determination of quantity rather than specific migration level should therefore be permitted under certain conditions.
- (14) For certain types of plastics the availability of generally recognised diffusion models based on experimental data allows the estimation of the migration level of a substance under certain conditions, therefore avoiding complex, costly and time-consuming testing.
- (15) The overall migration limit is a measure of the inertness of the material and prevents an unacceptable change in the composition of the foodstuffs, and, moreover, reduces the need for a large number of specific migration limits or other restrictions, thus giving effective control.
- (16) Council Directive 78/142/EEC<sup>(6)</sup> lays down limits for the quantity of vinyl chloride present in plastic materials and articles prepared with this substance and for the quantity of vinyl chloride released by these materials and articles, and Commission Directives 80/766/EEC<sup>(7)</sup> and 81/432/EEC<sup>(8)</sup> establish the Community methods of analysis for controlling these limits.
- (17) In view of potential liability, there is a need for the written declaration provided for in Article 6(5) of Directive 89/109/EEC whenever professional use is made of plastic materials and articles which are not by their nature clearly intended for food use.
- (18) Commission Directive 80/590/EEC<sup>(9)</sup> determines the symbol that may accompany any material and article intended to come into contact with foodstuffs.

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

- (19) In accordance with the principle of proportionality, it is necessary and appropriate for the achievement of the basic objective of ensuring the free movement of plastic materials and articles intended to come into contact with foodstuffs, to lay down rules on the definition of plastics and permitted substances. This Directive confines itself to what is necessary in order to achieve the objectives pursued in accordance with the third paragraph of Article 5 of the Treaty.
- (20) In accordance with Article 3 of Directive 89/109/EEC, the Scientific Committee on Food has been consulted on the provisions liable to affect public health.
- (21) The measures provided for in this Directive are in accordance with the opinion of the Standing Committee on the Food Chain and Animal Health.
- (22) This Directive should be without prejudice to the deadlines set out in Annex VII, Part B within which the Member States are to comply with Directive 90/128/EEC, and the acts amending it,

HAS ADOPTED THIS DIRECTIVE:

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

*Article 1*

1 This Directive is a specific Directive within the meaning of Article 3 of Directive 89/109/EEC.

2 This Directive shall apply to plastic materials and articles and parts thereof:

- a consisting exclusively of plastics; or
- b composed of two or more layers of materials, each consisting exclusively of plastics, which are bound together by means of adhesives or by any other means,

which, in the finished product state, are intended to come into contact or are brought into contact with foodstuffs and are intended for that purpose.

3 For the purposes of this Directive, ‘plastics’ shall mean the organic macromolecular compounds obtained by polymerisation, polycondensation, polyaddition or any other similar process from molecules with a lower molecular weight or by chemical alteration of natural macromolecules. Other substances or matter may be added to such macromolecular compounds.

However, the following shall not be regarded as ‘plastics’:

- a varnished or unvarnished regenerated cellulose film, covered by Commission Directive 93/10/EEC<sup>(10)</sup>;
- b elastomers and natural and synthetic rubber;
- c paper and paperboard, whether modified or not by the addition of plastics;
- d surface coatings obtained from:
  - paraffin waxes, including synthetic paraffin waxes, and/or micro-crystalline waxes,

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

- mixtures of the waxes listed in the first indent with each other and/or with plastics,
- e ion-exchange resins;
- f silicones.

4 This Directive shall not apply, until further action by the Commission, to materials and articles composed of two or more layers, one or more of which does not consist exclusively of plastics, even if the one intended to come into direct contact with foodstuffs does consist exclusively of plastics.

---

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

*Article 2*

Plastic materials and articles shall not transfer their constituents to foodstuffs in quantities exceeding 10 milligrams per square decimetre of surface area of material or article (mg/dm<sup>2</sup>) (overall migration limit). However, this limit shall be 60 milligrams of the constituents released per kilogram of foodstuff (mg/kg) in the following cases:

- (a) articles which are containers or are comparable to containers or which can be filled, with a capacity of not less than 500 millilitres (ml) and not more than 10 litres (l);
- (b) articles which can be filled and for which it is impracticable to estimate the surface area in contact with foodstuffs;
- (c) caps, gaskets, stoppers or similar devices for sealing.

---

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

*Article 3*

[<sup>F1</sup> Only those monomers and other starting substances listed in Annex II, section A may be used for the manufacture of plastic materials and articles subject to the restrictions set out therein.

2 By way of derogation from paragraph 1, the monomers and other starting substances listed in Annex II, section B may continue to be used until 31 December 2004 at the latest, pending their evaluation by the European Food Safety Authority (hereinafter referred to as the Authority).]

3 The list in Annex II, Section A, may be amended:

- either by adding substances listed in Annex II, Section B, according to the criteria in Annex II of Directive 89/109/EEC, or
- by including ‘new substances’, i.e. substances which are listed neither in Section A nor in Section B of Annex II, according to Article 3 of Directive 89/109/EEC.

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

4 No Member State shall authorise any new substance for use within its territory except under the procedure in Article 4 of Directive 89/109/EEC.

5 The lists appearing in Annex II, Sections A and B, do not yet include monomers and other starting substances used only in the manufacture of:

- surface coatings obtained from resinous or polymerised products in liquid, powder or dispersion form, such as varnishes, lacquers, paints, etc.,
- epoxy resins,
- adhesives and adhesion promoters,
- printing inks.

---

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

---

**Textual Amendments**

- F1** Substituted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).

*<sup>F1</sup>Article 4*

1 A list of additives which may be used for the manufacture of plastic materials and articles, together with the restrictions and/or specifications on their use, is set out in Annex III.

That list of additives shall be considered to be an incomplete list until the Commission decides, in accordance with Article 4a, that it shall become a positive Community list of authorised additives, to the exclusion of all others.

The Commission shall establish, by 31 December 2007 at the latest, the date when that list shall become a positive list.

2 For the additives listed in Annex III, section B, the verification of compliance with the specific migration limits in simulatant D or in test media of substitute tests as laid down in Article 3(1), second subparagraph of Directive 82/711/EEC and Article 1 of Directive 85/572/EEC shall apply from 1 July 2006.

3 The lists in Annex III, sections A and B do not yet include the following additives:

- a additives used only in the manufacture of:
  - surface coatings obtained from resinous or polymerised products in liquid, powder or dispersion form, such as varnishes, lacquers, paints,
  - epoxy resins,
  - adhesives and adhesion promoters,
  - printing inks;
- b colorants;
- c solvents.]

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

#### Editorial Information

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

#### Textual Amendments

- F1** Substituted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).

### *[<sup>F2</sup>Article 4a*

1 A new additive may always be added to the list of substances referred to in Article 4(1) following an evaluation of its safety by the Authority.

2 Member States shall provide that any person interested in the inclusion in the list referred to in Article 4(1) of an additive, which is already placed on the market in one or more of the Member States, shall submit data for the evaluation of its safety by the Authority by 31 December 2006 at the latest.

For the submission of the required data, the applicant shall consult the ‘Guidelines of the European Food Safety Authority for the presentation of an application for safety assessment of a substance to be used in food contact materials prior to its authorisation’.

3 If during the examination of the data referred to in paragraph 2, the Authority calls for supplementary information, the additive may continue to be used subject to national law until the Authority has issued an opinion, provided that the information is submitted within the time limits specified by the Authority.

4 The Commission shall establish, by 31 December 2007 at the latest, a provisional list of additives which may continue to be used after 31 December 2007 subject to national law until the Authority has evaluated them.

5 The inclusion of an additive in the provisional list is subject to the following conditions:

- a the additive must be permitted in one or more of the Member States no later than 31 December 2006;
- b the data referred to in paragraph 2 concerning that additive must have been supplied in accordance with the Authority requirements no later than 31 December 2006.

#### Editorial Information

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

#### Textual Amendments

- F2** Inserted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

#### Article 4b

Without prejudice to Article 4 of Directive 89/109/EEC, Member States may not authorise after 31 December 2006 additives referred to in Article 4(1) which were never evaluated by the Scientific Committee on Food or the Authority.]

##### Editorial Information

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

##### Textual Amendments

- F2** Inserted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).

#### Article 5

Only the products obtained by means of bacterial fermentation listed in Annex IV may be used in contact with foodstuffs.

##### Editorial Information

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

#### <sup>F2</sup>Article 5a

5 Additives referred to in Article 4, which are authorised as food additives by Council Directive 89/107/EEC<sup>(11)</sup> or flavourings by Council Directive 88/388/EEC<sup>(12)</sup> shall not migrate into:

- a foodstuffs in quantities having a technological function in the final foodstuffs;
- b foodstuffs for which their use is authorised as food additives or flavourings, in quantities exceeding the restrictions provided for in Directive 89/107/EEC or in Directive 88/388/EEC or in Article 4 of this Directive, whichever is the lower;
- c foodstuffs for which their use is not authorised as food additives or flavourings, in quantities exceeding the restrictions set out in Article 4 of this Directive.

2 At the marketing stages other than the retail stages, plastic materials and articles which are intended to be placed in contact with foodstuffs and which contain additives referred to in paragraph 1 shall be accompanied by a written declaration containing the information referred to in Article 9(1)(b).

3 By way of derogation from paragraph 1, when the substances referred to in point (a) of paragraph 1 are used as active components of active food contact materials and articles, they may be subject to national provisions pending the adoption of Community provisions.]

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

**Textual Amendments**

- F2** Inserted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).

*Article 6*

1 General specifications related to plastic materials and articles are laid down in Annex V, Part A. Other specifications related to some substances appearing in Annexes II, III and IV are laid down in Annex V, Part B.

2 The meaning of the numbers between brackets appearing in the column ‘Restrictions and/or specifications’ is explained in Annex VI.

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

*[<sup>F1</sup>Article 7*

The specific migration limits in the list set out in Annexes II and III are expressed in mg/kg. However, such limits are expressed in mg/dm<sup>2</sup> in the following cases:

- (a) articles which are containers or are comparable to containers or which can be filled, with a capacity of less than 500 ml or more than 10 l;
- (b) sheet, film or other material or articles which cannot be filled or for which it is impracticable to estimate the relationship between the surface area of such material or article and the quantity of food in contact therewith.

In those cases, the limits set out in Annexes II and III, expressed in mg/kg shall be divided by the conventional conversion factor of 6 in order to express them in mg/dm<sup>2</sup>.]

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

**Textual Amendments**

- F1** Substituted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).



*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

### Article 8

1 Verification of compliance with the migration limits shall be carried out in accordance with the rules laid down in Directives 82/711/EEC and 85/572/EEC and the further provisions set out in Annex I.

[<sup>F12</sup> The verification of compliance with the specific migration limits provided for in paragraph 1 shall not be compulsory, if the value of overall migration determination implies that the specific migration limits referred to in that paragraph are not exceeded.]

3 The verification of compliance with the specific migration limits provided for in paragraph 1 shall not be compulsory, if it can be established that, by assuming complete migration of the residual substance in the material or article, it cannot exceed the specific limit of migration.

4 The verification of compliance with the specific migration limits provided for in paragraph 1 may be ensured by the determination of the quantity of a substance in the finished material or article provided that a relationship between that quantity and the value of the specific migration of the substance has been established either by an adequate experimentation or by the application of generally recognised diffusion models based on scientific evidence. To demonstrate the non-compliance of a material or article, confirmation of the estimated migration value by experimental testing is obligatory.

#### Editorial Information

**X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

#### Textual Amendments

**F1** Substituted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).

### Article 9

[<sup>F11</sup> At the marketing stages other than the retail stages, plastic materials and articles which are intended to be placed in contact with foodstuffs shall be accompanied by a written declaration, which shall:

- a be in accordance with Article 6(5) of Directive 89/109/EEC;
- b provide, for substances which are subject to a restriction in food, adequate information obtained by experimental data or theoretical calculation about the level of their specific migration and, where appropriate, purity criteria in accordance with Commission Directives 95/31/EC<sup>(13)</sup>, 95/45/EC<sup>(14)</sup> and 2002/82/EC<sup>(15)</sup> to enable the user of these materials and articles to comply with the relevant Community provisions or, in their absence, with national provisions applicable to food.]

<sup>F32</sup> .....

#### Editorial Information

**X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

**Textual Amendments**

- F1** Substituted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).
- F3** Deleted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).

*Article 10*

1 Directive 90/128/EEC, as amended by the Directives set out in Annex VII, Part A, is hereby repealed without prejudice to the obligations of the Member States in respect of the deadlines for transposition and application laid down in Annex VII, Part B.

2 References to the repealed Directives shall be construed as references to this Directive and be read in accordance with the correlation table set out in Annex VIII.

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

*Article 11*

This Directive shall enter into force on the 20th day following that of its publication in the *Official Journal of the European Communities*.

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

*Article 12*

This Directive is addressed to the Member States.

**Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

## ANNEX I

FURTHER PROVISIONS APPLICABLE WHEN CHECKING  
COMPLIANCE WITH THE MIGRATION LIMITS

## General provisions

1. When comparing the results of the migration tests specified in the Annex to Directive 82/711/EEC, the specific gravity of all the simulants should conventionally be assumed to be 1. Milligrams of substance(s) released per litre of simulant (mg/l) will thus correspond numerically to milligrams of substance(s) released per kilogram of simulant and, taking into account the provisions laid down in Directive 85/572/EEC, to milligrams of substance(s) released per kilogram of foodstuff.
2. Where the migration tests are carried out on samples taken from the material or article or on samples manufactured for the purpose, and the quantities of foodstuff or simulant placed in contact with the sample differ from those employed in the actual conditions under which the material or article is used, the results obtained should be corrected by applying the following formula:

$$M = \frac{m \cdot a_2}{a_1 \cdot q} \cdot 1\,000$$

Where:

- |                |   |
|----------------|---|
| M              | is the migration in mg/kg;  |
| m              | is the mass in mg of substance released by the sample as determined by the migration test;                                |
| a <sub>1</sub> | is the surface area in dm <sup>2</sup> of the sample in contact with the foodstuff or simulant during the migration test; |
| a <sub>2</sub> | is the surface area in dm <sup>2</sup> of the material or article in real conditions of use;                              |
| q              | is the quantity in grams of foodstuff in contact with the material or article in real conditions of use.                  |

3. The determination of migration is carried out on the material or article or, if that is impracticable, using either specimens taken from the material or article or, where appropriate, specimens representative of this material or article.

The sample shall be placed in contact with the foodstuff or simulant in a manner representing the contact conditions in actual use. For this purpose, the test shall be performed in such a way that only those parts of the sample intended to come into contact with foodstuffs in actual use will be in contact with the foodstuff or simulant. This condition is particularly important in the case of materials and articles comprising several layers, for closures, etc.

The migration testing of caps, gaskets, stoppers or similar devices for sealing must be carried out on these articles by applying them to the containers for which they are intended in a manner which corresponds to the conditions of closing in normal or foreseeable use.

It shall in all cases be permissible to demonstrate compliance with migration limits by the use of a more severe test.

4. In accordance with the provisions set out in Article 8 of the present Directive, the sample of the material or article is placed in contact with the foodstuff or appropriate simulant for a period and at a temperature which are chosen by reference to the contact conditions in actual use, in accordance with the rules laid down in Directives 82/711/EEC and 85/572/EEC. At the end of the prescribed time, the analytical determination of the total quantity of substances (overall migration) and/or the specific quantity of

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

one or more substances (specific migration) released by the sample is carried out on the foodstuff or simulant.

5. Where a material or article is intended to come into repeated contact with foodstuffs, the migration test(s) shall be carried out three times on a single sample in accordance with the conditions laid down in Directive 82/711/EEC using another sample of the food or simulant(s) on each occasion. Its compliance shall be checked on the basis of the level of the migration found in the third test. However, if there is conclusive proof that the level of the migration does not increase in the second and third tests and if the migration limit(s) is (are) not exceeded on the first test, no further test is necessary.

Special provisions relating to overall migration

6. If the aqueous simulants specified in Directives 82/711/EEC and 85/572/EEC are used, the analytical determination of the total quantity of substances released by the sample may be carried out by evaporation of the simulant and weighing of the residue.

If rectified olive oil or any of its substitutes is used, the procedure given below may be followed.

The sample of the material or article is weighed before and after contact with the simulant. The simulant absorbed by the sample is extracted and determined quantitatively. The quantity of simulant found is subtracted from the weight of the sample measured after contact with the simulant. The difference between the initial and corrected final weights represents the overall migration of the sample examined.

Where a material or article is intended to come into repeated contact with foodstuffs and it is technically impossible to carry out the test described in paragraph 5, modifications to that test are acceptable, provided that they enable the level of migration occurring during the third test to be determined. One of these possible modifications is described below.

The test is carried out on three identical samples of the material or article. One of these shall be subjected to the appropriate test and the overall migration determined ( $M_1$ ). The second and third samples shall be subjected to the same conditions of temperature but the period of contact shall be two and three times that specified and overall migration determined in each case ( $M_2$  and  $M_3$ , respectively).

The material or article shall be deemed to be in compliance provided that either  $M_1$  or  $M_3 - M_2$  does not exceed the overall migration limit.

7. A material or article that exceeds the overall migration limit by an amount not greater than the analytical tolerance mentioned below should therefore be deemed to be in compliance with this Directive.

The following analytical tolerances have been observed:

- 20 mg/kg or 3 mg/dm<sup>2</sup> in migration tests using rectified olive oil or substitutes,
- 12 mg/kg or 2 mg/dm<sup>2</sup> in migration tests using the other simulants referred to in Directives 82/711/EEC and 85/572/EEC.

8. Without prejudice to the provisions of Article 3(2) of Directive 82/711/EEC, migration tests using rectified olive oil or substitutes shall not be carried out to check compliance with the overall migration limit in cases where there is conclusive proof that the specified analytical method is inadequate from a technical standpoint.

In any such case, for substances exempt from specific migration limits or other restrictions in the list provided in Annex II, a generic specific migration limit of 60 mg/kg or 10 mg/dm<sup>2</sup>,

according to the case, is applied. However, the sum of all specific migrations determined shall not exceed the overall migration limit.

## ANNEX II

### LIST OF MONOMERS AND OTHER STARTING SUBSTANCES WHICH MAY BE USED IN THE MANUFACTURE OF PLASTIC MATERIALS AND ARTICLES GENERAL INTRODUCTION

1. This Annex contains the list of monomers or other starting substances. The list includes:
  - substances undergoing polymerisation, which includes polycondensation, polyaddition or any other similar process, to manufacture macromolecules,
  - natural or synthetic macromolecular substances used in the manufacture of modified macromolecules, if the monomers or the other starting substances required to synthesise them are not included in the list,
  - substances used to modify existing natural or synthetic macromolecular substances.
- [<sup>F4</sup>2. The following substances are not included even if they are intentionally used and are authorised:
  - (a) salts (including double salts and acid salts) of aluminium, ammonium, calcium, iron, magnesium, potassium and sodium of authorised acids, phenols or alcohols. However, names containing ‘... acid(s), salts’ appear in the lists, if the corresponding free acid(s) is (are) not mentioned;
  - (b) salts (including double salts and acid salts) of zinc of authorised acids, phenols or alcohols. For these salts a Group SML = 25 mg/kg (expressed as Zn) apply. The same restriction for Zn applies to:
    - (i) substances whose name contains ‘... acid(s), salts’ which appear in the lists, if the corresponding free acid(s) is (are) not mentioned,
    - (ii) substances referred to in note 38 of Annex VI.]

#### Textual Amendments

- F4** Substituted by [Commission Directive 2005/79/EC of 18 November 2005 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with food \(Text with EEA relevance\)](#).

3. The list also does not include the following substances although they may be present:
  - (a) substances which could be present in the finished product as:
    - impurities in the substances used,
    - reaction intermediates,
    - decomposition products;
  - (b) oligomers and natural or synthetic macromolecular substances as well as their mixtures, if the monomers or starting substances required to synthesise them are included in the list;

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

(c) mixtures of the authorised substances.

The materials and articles which contain the substances indicated under points (a), (b) and (c) shall comply with the requirements stated in Article 2 of Directive 89/109/EEC.

4. Substances shall be of good technical quality as regards the purity criteria.
5. The list contains the following information:
  - column 1 (Ref. No): the EEC packaging material reference number of the substances on the list,
  - column 2 (CAS No): the CAS (Chemical Abstracts Service) registry number,
  - column 3 (Name): the chemical name,
  - column 4 (Restrictions and/or specifications): These may include:
    - specific migration limit (SML),
    - maximum permitted quantity of the substance in the finished material or article (QM),
    - maximum permitted quantity of the substance in the finished material or article expressed as mg per 6 dm<sup>2</sup> of the surface in contact with foodstuffs (QMA),
    - any other restriction specifically mentioned,
    - any type of specifications related to the substance or to the polymer.
6. If a substance appearing on the list as an individual compound is also covered by a generic term, the restrictions applying to this substance shall be those indicated for the individual compound.
7. Where there is any inconsistency between the CAS number and the chemical name, the chemical name shall take precedence over the CAS number. If there is an inconsistency between the CAS number reported in EINECS and the CAS Registry, the CAS number in the CAS Registry shall apply.
8. A number of abbreviations or expressions are used in column 4 of the table, the meanings of which are as follows:
 

DL	=	Detection limit of the method of analysis;
FP	=	Finished material or article;
NCO	=	Isocyanate moiety;
ND	=	not detectable. For the purpose of this Directive 'not detectable' means that the substance should not be detected by a validated method of analysis which should detect it at the detection limit (DL) specified. If such a method does not currently exist, an analytical method with appropriate performance characteristics at the detection limit may be used, pending the development of a validated method;
[ <sup>F1</sup> QM	=	Maximum permitted quantity of the 'residual' substance in the material or article. For the purpose of this Directive the quantity of the substance in the material or article shall be determined by a validated method of analysis. If such a method does not currently exist, an analytical method with appropriate performance characteristics at the specified limit may be used, pending the development of a validated method;]
QM(T)	=	Maximum permitted quantity of the 'residual' substance in the material or article expressed as total of moiety or substance(s) indicated. For the purpose of this Directive the quantity of the substance in the material or article should be determined by a validated method of analysis. If such a method does not currently exist, an analytical method with appropriate

- performance characteristics at the specified limit may be used, pending the development of a validated method;
- QMA = Maximum permitted quantity of the ‘residual’ substance in the finished material or article expressed as mg per 6 dm<sup>2</sup> of the surface in contact with foodstuffs. For the purpose of this Directive the quantity of the substance in the surface of the material or article should be determined by a validated method of analysis. If such a method does not currently exist, an analytical method with appropriate performance characteristics at the specified limit may be used, pending the development of a validated method;
- QMA(T) = Maximum permitted quantity of the ‘residual’ substance in the material or article expressed as mg of total of moiety or substance(s) indicated per 6 dm<sup>2</sup> of the surface in contact with foodstuffs. For the purpose of this Directive the quantity of the substance in the surface of the material or article should be determined by a validated method of analysis. If such a method does not currently exist, an analytical method with appropriate performance characteristics at the specified limit may be used, pending the development of a validated method;
- SML = Specific migration limit in food or in food simulant, unless it is specified otherwise. For the purpose of this Directive the specific migration of the substance should be determined by a validated method of analysis. If such a method does not currently exist, an analytical method with appropriate performance characteristics at the specified limit may be used, pending the development of a validated method;
- SML(T) = Specific migration limit in food or in food simulant expressed as total of moiety or substance(s) indicated. For the purpose of this Directive the specific migration of the substances should be determined by a validated method of analysis. If such a method does not currently exist, an analytical method with appropriate performance characteristics at the specified limit may be used, pending the development of a validated method.

## Section A

## LIST OF AUTHORISED MONOMERS AND OTHER STARTING SUBSTANCES

Ref. No.	CAS No	Name	Restrictions and/or specifications
(1)	(2)	(3)	(4)
10030	000514-10-3	Abietic acid	
10060	000075-07-0	Acetaldehyde	SML(T) = 6 mg/kg (2)
10090	000064-19-7	Acetic acid	
10120	000108-05-4	Acetic acid, vinyl ester	SML = 12 mg/kg
10150	000108-24-7	Acetic anhydride	
10210	000074-86-2	Acetylene	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

[ <sup>F2</sup> 10599/90A	061788-89-4	Acids, fatty, unsaturated (C <sub>18</sub> ), dimers, distilled	QMA(T) = 0,05 mg/6 dm <sup>2</sup> ( <sup>27</sup> )
10599/91	061788-89-4	Acids, fatty, unsaturated (C <sub>18</sub> ), dimers, non distilled	QMA(T) = 0,05 mg/6 dm <sup>2</sup> ( <sup>27</sup> )
10599/92A	068783-41-5	Acids, fatty, unsaturated (C <sub>18</sub> ), dimers, hydrogenated, distilled	QMA(T) = 0,05 mg/6 dm <sup>2</sup> ( <sup>27</sup> )
10599/93	068783-41-5	Acids, fatty, unsaturated (C <sub>18</sub> ), dimers, hydrogenated, non distilled	QMA(T) = 0,05 mg/6 dm <sup>2</sup> ( <sup>27</sup> )
10630	000079-06-1	Acrylamide	SML = ND (DL = 0,01 mg/kg)
10660	015214-89-8	2-Acrylamido-2-methylpropanesulphonic acid	SML = 0,05 mg/kg
10690	000079-10-7	Acrylic acid	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
10750	002495-35-4	Acrylic acid, benzyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
10780	000141-32-2	Acrylic acid, n-butyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
10810	002998-08-5	Acrylic acid, sec-butyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
10840	001663-39-4	Acrylic acid, tert-butyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
[ <sup>F6</sup> ]			
[ <sup>F5</sup> 11005	012542-30-2	Acrylic acid, dicyclopentenyl ester	QMA = 0,05 mg/6 dm <sup>2</sup>
11245	002156-97-0	Acrylic acid, dodecyl ester	SML = 0,05 mg/kg ( <sup>1</sup> )
11470	000140-88-5	Acrylic acid, ethyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
[ <sup>F5</sup> 11500	000103-11-7	Acrylic acid, 2-ethylhexyl ester	SML = 0,05 mg/kg]



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

11510	000818-61-1	Acrylic acid, hydroxyethyl ester	See 'Acrylic acid, monoester with ethyleneglycol'
11530	[ <sup>F1</sup> 00999-61-1]	Acrylic acid, 2-hydroxypropyl ester	[ <sup>F1</sup> QMA = 0,05 mg/6 dm <sup>2</sup> for the sum of acrylic acid, 2-hydroxypropyl ester and acrylic acid, 2-hydroxyisopropyl ester and in compliance with the specifications laid down in Annex V]
11590	000106-63-8	Acrylic acid, isobutyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
11680	000689-12-3	Acrylic acid, isopropyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
11710	000096-33-3	Acrylic acid, methyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
11830	000818-61-1	Acrylic acid, monoester with ethyleneglycol	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
11890	002499-59-4	Acrylic acid, n-octyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
11980	000925-60-0	Acrylic acid, propyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>36</sup> )]
12100	000107-13-1	Acrylonitrile	SML = ND (DL= 0,020 mg/kg, analytical tolerance included)
12130	000124-04-9	Adipic acid	
12265	004074-90-2	Adipic acid, divinyl ester	QM = 5 mg/kg in FP. Or use only as comonomer
12280	002035-75-8	Adipic anhydride	
12310		Albumin	
12340		Albumin, coagulated by formaldehyde	
12375		Alcohols, aliphatic, monohydric,	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

		saturated, linear, primary (C <sub>4</sub> -C <sub>22</sub> )	
12670	002855-13-2	1-Amino-3-aminomethyl-3,5,5-trimethylcyclohexane	SML = 6 mg/kg
12761	000693-57-2	12-Aminododecanoic acid	SML= 0,05 mg/kg
12763	000141-43-5	2-Aminoethanol	SML = 0,05 mg/kg. Not for use in polymers contacting foods for which simulant D is laid down in Directive 85/572/EEC and for indirect food contact only, behind the PET layer
12765	084434-12-8	N-(2-Aminoethyl)-beta-alanine, sodium salt	SML= 0,05 mg/kg
[ <sup>F5</sup> 12786	000919-30-2	3-Aminopropyltriethoxysilane	Residual extractable content of 3-aminopropyltriethoxysilane to be less than 3 mg/kg filler. To be used only for the reactive surface treatment of inorganic fillers]
12788	002432-99-7	11-Aminoundecanoic acid	SML= 5 mg/kg
12789	007664-41-7	Ammonia	
12820	000123-99-9	Azelaic acid	
12970	004196-95-6	Azelaic anhydride	
13000	001477-55-0	1,3-Benzenedimethanamine	SML= 0,05 mg/kg
13060	004422-95-1	1,3,5-Benzenetricarboxylic acid trichloride	QMA = 0,05 mg/6 dm <sup>2</sup> (measured as 1,3,5-Benzenetricarboxylic acid)
13075	000091-76-9	Benzoguanamine	See '2,4-Diamino-6-phenyl-1,3,5-triazine'
13090	000065-85-0	Benzoic acid	
13150	000100-51-6	Benzyl alcohol	

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

13180	000498-66-8	Bicyclo[2.2.1]hept-2-ene (=Norbornene)	SML= 0,05 mg/kg
13210	001761-71-3	Bis(4-aminocyclohexyl)methane	SML= 0,05 mg/kg
[ <sup>F5</sup> 13317	132459-54-2	N,N'-Bis[4-(ethoxycarbonyl)phenyl]naphthalenetetracarboxylic diimide	SML = 0,05 mg/kg. Purity >= 98,1 % (w/w) diimide used only as co-monomer (max 4 %) for polyesters (PET, PBT)]
[ <sup>F2</sup> 13323	000102-40-9	1,3-Bis(2-hydroxyethoxy)benzene	SML = 0,05 mg/kg]
13326	000111-46-6	Bis(2-hydroxyethyl)ether	See 'Diethyleneglycol'
13380	000077-99-6	2,2-Bis(hydroxymethyl)-1-butanol	See '1,1,1-Trimethylolpropane'
13390	000105-08-8	1,4-Bis(hydroxymethyl)cyclohexane	
13395	004767-03-7	2,2-Bis(hydroxymethyl)propionic acid	QMA = 0,05 mg/6 dm <sup>2</sup>
13480	000080-05-7	2,2-Bis(4-hydroxyphenyl)propane	[ <sup>F1</sup> SML(T) = 0,6 mg/kg ( <sup>28</sup> )]
13510	001675-54-3	2,2-Bis(4-hydroxyphenyl)propane bis(2,3-epoxypropyl) ether (=BADGE)	According to Commission Directive 2002/16/EC of 20 February 2002 on the use of certain epoxy derivatives in materials and articles intended to come into contact with foodstuffs (OJ L 51, 22.2.2002, p. 27)
13530	038103-06-9	2,2-Bis(4-hydroxyphenyl)propane bis(phthalic anhydride)	SML = 0,05 mg/kg
13550	000110-98-5	Bis(hydroxypropyl) ether	See 'Dipropyleneglycol'
13560	0005124-30-1	Bis(4-isocyanatocyclohexyl)methane	See 'Bis(4-aminocyclohexyl)methane-4,4'-diisocyanate'

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

13600	047465-97-4	3,3-Bis(3-methyl-4-hydroxyphenyl)2-indolinone	SML = 1,8 mg/kg
13607	000080-05-7	Bisphenol A	See '2,2-Bis(4-hydroxyphenyl)propane'
13610	001675-54-3	Bisphenol A bis(2,3-epoxypropyl) ether	See '2,2-Bis(4-hydroxyphenyl)propane bis(2,3-epoxypropyl) ether'
13614	038103-06-9	Bisphenol A bis(phthalic anhydride)	See '2,2-Bis(4-hydroxyphenyl)propane bis(phthalic anhydride)'
13617	000080-09-1	Bisphenol S	See '4,4'-Dihydroxydiphenyl sulphone'
13620	010043-35-3	Boric acid	SML(T) = 6 mg/kg <sup>(23)</sup> (expressed as Boron) without prejudice to the provisions of Directive 98/83/EC on water for human consumption (OJ L 330, 5.12.1998, p. 32).
13630	000106-99-0	Butadiene	QM = 1 mg/kg in FP or SML = not detectable (DL = 0,020 mg/kg, analytical tolerance included)
13690	000107-88-0	1,3-Butanediol	
13720	000110-63-4	1,4-Butanediol	[ <sup>F4</sup> SML(T) = 5 mg/kg <sup>(24)</sup> ]
13780	002425-79-8	1,4-Butanediol bis(2,3-epoxypropyl)ether	QM = 1 mg/kg in FP (expressed as Epoxy group, Mw = 43)
13810	000505-65-7	1,4-Butanediol formal	QMA = 0,05 mg/6 dm <sup>2</sup>
13840	000071-36-3	1-Butanol	
13870	000106-98-9	1-Butene	
13900	000107-01-7	2-Butene	

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

13932	000598-32-3	3-Buten-2-ol	QMA = ND (DL = 0,02 mg/6 dm <sup>2</sup> ) To be used only as a comonomer for the preparation of polymeric additive
14020	000098-54-4	4-tert-Butylphenol	SML = 0,05 mg/kg
14110	000123-72-8	Butyraldehyde	
14140	000107-92-6	Butyric acid	
14170	000106-31-0	Butyric anhydride	
14200	000105-60-2	Caprolactam	SML(T) = 15 mg/ kg ( <sup>5</sup> )
14230	002123-24-2	Caprolactam, sodium salt	SML(T) = 15 mg/ kg ( <sup>5</sup> ) (expressed as Caprolactam)
[ <sup>F5</sup> 14260	000502-44-3	Caprolactone	SML = 0,05 mg/kg (expressed as the sum of caprolactone and 6-hydroxyhexanoic acid)]
14320	000124-07-2	Caprylic acid	
14350	000630-08-0	Carbon monoxide	
14380	000075-44-5	Carbonyl chloride	QM = 1 mg/kg in FP
14411	008001-79-4	Castor oil	
14500	009004-34-6	Cellulose	
14530	007782-50-5	Chlorine	
14570	000106-89-8	1-Chloro-2,3- epoxypropane	See 'Epichlorohydrin'
14650	000079-38-9	Chlorotrifluoroethylene	QMA = 0,5 mg/6 dm <sup>2</sup>
14680	000077-92-9	Citric acid	
14710	000108-39-4	<i>m</i> -Cresol	
14740	000095-48-7	<i>o</i> -Cresol	
14770	000106-44-5	<i>p</i> -Cresol	
[ <sup>F2</sup> 14800	003724-65-0	Crotonic acid	QMA(T) = 0,05 mg/6 dm <sup>2</sup> ( <sup>33</sup> )]
14841	000599-64-4	4-Cumylphenol	SML = 0,05 mg/kg
14880	000105-08-8	1,4- Cyclohexanedimethano	See '1,4- Bis(hydroxymethyl)cyclohexane'

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

14950	003173-53-3	Cyclohexyl isocyanate	[ <sup>F1</sup> QM(T) = 1 mg/kg in FP (expressed as NCO) ( <sup>26</sup> )]
15030	000931-88-4	Cyclooctene	SML = 0,05 mg/kg. For use only in polymers contacting foods for which simulant A is laid down in Directive 85/572/EEC
15070	001647-16-1	1,9-Decadiene	SML = 0,05 mg/kg
15095	000334-48-5	Decanoic acid	
15100	000112-30-1	1-Decanol	
15130	000872-05-9	1-Decene	SML = 0,05 mg/kg
15250	000110-60-1	1,4-Diaminobutane	
15272	000107-15-3	1,2-Diaminoethane	See 'Ethylenediamine'
15274	000124-09-4	1,6-Diaminohexane	See 'Hexamethylenediamine'
15310	000091-76-9	2,4-Diamino-6-phenyl-1,3,5-triazine	QMA = 5 mg/6 dm <sup>2</sup>
[ <sup>F3</sup>			
<sup>F3</sup> ]			
15565	000106-46-7	1,4-Dichlorobenzene	SML = 12 mg/kg
15610	000080-07-9	4,4'-Dichlorodiphenyl sulphone	SML = 0,05 mg/kg
15700	005124-30-1	Dicyclohexylmethane-4,4'-diisocyanate	QM(T) = 1 mg/kg (expressed as NCO ( <sup>26</sup> ))
15760	000111-46-6	Diethyleneglycol	SML(T) = 30 mg/kg ( <sup>3</sup> )
15790	000111-40-0	Diethylenetriamine	SML = 5 mg/kg
15820	000345-92-6	4,4'-Difluorobenzophenone	SML = 0,05 mg/kg
15880	000120-80-9	1,2-Dihydroxybenzene	SML = 6 mg/kg
15910	000108-46-3	1,3-Dihydroxybenzene	SML = 2,4 mg/kg

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

15940	000123-31-9	1,4-Dihydroxybenzene	SML = 0,6 mg/kg
15970	000611-99-4	4,4'-Dihydroxybenzophenone	SML(T) = 6 mg/kg <sup>(15)</sup>
16000	000092-88-6	4,4'-Dihydroxybiphenyl	SML = 6 mg/kg
16090	000080-09-1	4,4'-Dihydroxydiphenyl sulphone	SML = 0,05 mg/kg
16150	000108-01-0	Dimethylaminoethanol	SML = 18 mg/kg
[ <sup>F2</sup> 16210	006864-37-5	3,3'-Dimethyl-4,4'-diaminodicyclohexylmethane	SML = 0,05 mg/kg [to be used only in polyamides.]
16240	000091-97-4	3,3'-Dimethyl-4,4'-diisocyanatobiphenyl	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
16360	000576-26-1	2,6-Dimethylphenol	SML = 0,05 mg/kg
16390	000126-30-7	2,2-Dimethyl-1,3-propanediol	SML = 0,05 mg/kg
16450	000646-06-0	1,3-Dioxolane	SML = 0,05 mg/kg
16480	000126-58-9	Dipentaerythritol	
[ <sup>F2</sup> 16540	000102-09-0	Diphenyl carbonate	SML = 0,05 mg/kg]
16570	004128-73-8	Diphenylether-4,4'-diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
16600	005873-54-1	Diphenylmethane-2,4'-diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
16630	000101-68-8	Diphenylmethane-4,4'-diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
16650	000127-63-9	Diphenyl sulphone	SML(T) = 3 mg/kg <sup>(25)</sup>
16660	000110-98-5	Dipropyleneglycol	
16690	001321-74-0	Divinylbenzene	QMA = 0,01 mg/6 dm <sup>2</sup> or SML = ND (DL = 0,02 mg/kg, analytical tolerance included) for the sum of divinylbenzene and

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

			ethylvinylbenzene and in compliance with the specifications laid down in Annex V
16694	013811-50-2	N,N'-Divinyl-2-imidazolidinone	QM = 5 mg/kg in FP
16697	000693-23-2	n-Dodecanedioic acid	
16704	000112-41-4	1-Dodecene	SML = 0,05 mg/kg
16750	000106-89-8	Epichlorohydrin	QM = 1 mg/kg in FP
16780	000064-17-5	Ethanol	
16950	000074-85-1	Ethylene	
[ <sup>F5</sup> 16955	000096-49-1	Ethylene carbonate	Residual content = 5 mg/kg of hydrogel at a maximum ratio of 10 g of hydrogel to 1 kg of food. The hydrolysate contains ethyleneglycol having an SML = 30 mg/kg]
16960	000107-15-3	Ethylenediamine	SML = 12 mg/kg
16990	000107-21-1	Ethyleneglycol	SML(T) = 30 mg/kg <sup>(3)</sup>
17005	000151-56-4	Ethylenimine	SML = ND (DL = 0,01 mg/kg)
17020	000075-21-8	Ethylene oxide	QM = 1 mg/kg in FP
17050	000104-76-7	2-Ethyl-1-hexanol	SML = 30 mg/kg
[ <sup>F2</sup> 17110	016219-75-3	5-Ethylidenebicyclo[2,2,1]hept-2-ene	QMA 1,05 mg/6 dm <sup>2</sup> . The ratio surface/quantity of food shall be lower than 2 dm <sup>2</sup> /kg]
17160	000097-53-0	Eugenol	SML = ND (DL = 0,02 mg/kg, analytical tolerance included)
17170	061788-47-4	Fatty acids, coco	
17200	068308-53-2	Fatty acids, soya	
17230	061790-12-3	Fatty acids, tall oil	
17260	000050-00-0	Formaldehyde	SML(T) = 15 mg/kg <sup>(22)</sup>



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

17290	000110-17-8	Fumaric acid	
17530	000050-99-7	Glucose	
18010	000110-94-1	Glutaric acid	
18070	000108-55-4	Glutaric anhydride	
18100	000056-81-5	Glycerol	
18220	068564-88-5	N-Heptylamino undecanoic acid	SML = 0,05 mg/kg <sup>(1)</sup>
18250	000115-28-6	Hexachloroendomethylenetetrahydrophthalic acid	SML = ND (DL = 0,01 mg/kg)
18280	000115-27-5	Hexachloroendomethylenetetrahydrophthalic anhydride	SML = ND (DL = 0,01 mg/kg)
18310	036653-82-4	1-Hexadecanol	
18430	000116-15-4	Hexafluoropropylene	SML = ND (DL = 0,01 mg/kg)
18460	000124-09-4	Hexamethylenediamine	SML = 2,4 mg/kg
18640	000822-06-0	Hexamethylene diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
18670	000100-97-0	Hexamethylenetetramine	SML(T) = 15 mg/kg <sup>(22)</sup> (expressed as Formaldehyde)
[ <sup>F2</sup> 18700	000629-11-8	1,6-Hexanediol	SML = 0,05 mg/kg]
18820	000592-41-6	1-Hexene	SML = 3 mg/kg
18867	000123-31-9	Hydroquinone	See '1,4-Dihydroxybenzene'
18880	000099-96-7	p-Hydroxybenzoic acid	
[ <sup>F2</sup> 18896	001679-51-2	4-(Hydroxymethyl)-1-cyclohexene	SML = 0,05 mg/kg]
18897	016712-64-4	6-Hydroxy-2-naphthalenecarboxylic acid	SML = 0,05 mg/kg
18898	000103-90-2	N-(4-Hydroxyphenyl) acetamide	[ <sup>F1</sup> SML = 0,05 mg/kg]
19000	000115-11-7	Isobutene	
19060	000109-53-5	Isobutyl vinyl ether	QM = 5 mg/kg in FP

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

19110	004098-71-9	1-Isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
19150	000121-91-5	Isophthalic acid	SML = 5 mg/kg
19210	001459-93-4	Isophthalic acid, dimethyl ester	SML = 0,05 mg/kg
19243	000078-79-5	Isoprene	See '2-Methyl-1,3-butadiene'
19270	000097-65-4	Itaconic acid	
19460	000050-21-5	Lactic acid	
19470	000143-07-7	Lauric acid	
19480	002146-71-6	Lauric acid, vinyl ester	
19490	000947-04-6	Laurolactam	SML = 5 mg/kg
19510	011132-73-3	Lignocellulose	
19540	000110-16-7	Maleic acid	SML(T) = 30 mg/kg <sup>(4)</sup>
19960	000108-31-6	Maleic anhydride	SML(T) = 30 mg/kg <sup>(4)</sup> (expressed as maleic acid)
19975	000108-78-1	Melamine	See '2,4,6-triamino-1,3,5-triazine'
19990	000079-39-0	Methacrylamide	SML = ND (DL = 0,02 mg/kg, analytical tolerance included)
20020	000079-41-4	Methacrylic acid	[ <sup>F5</sup> SML(T) = 6 mg/kg <sup>(37)</sup> ]
20050	000096-05-9	Methacrylic acid, allyl ester	SML = 0,05 mg/kg
20080	002495-37-6	Methacrylic acid, benzyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg <sup>(37)</sup> ]
20110	000097-88-1	Methacrylic acid, butyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg <sup>(37)</sup> ]
20140	002998-18-7	Methacrylic acid, sec-butyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg <sup>(37)</sup> ]
20170	000585-07-9	Methacrylic acid, tert-butyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg <sup>(37)</sup> ]

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

20260	000101-43-9	Methacrylic acid, cyclohexyl ester	SML = 0,05 mg/kg
20410	002082-81-7	Methacrylic acid, diester with 1,4-butanediol	SML = 0,05 mg/kg
[ <sup>F2</sup> 20440	000097-90-5	Methacrylic acid, diester with ethyleneglycol	SML = 0,05 mg/kg]
20530	002867-47-2	Methacrylic acid, 2-(dimethylamino)-ethyl ester	SML = ND (DL = 0,02 mg/kg, analytical tolerance included)
20590	000106-91-2	Methacrylic acid, 2,3-epoxypropyl ester	QMA = 0,02 mg/6 dm <sup>2</sup>
20890	000097-63-2	Methacrylic acid, ethyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
21010	000097-86-9	Methacrylic acid, isobutyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
21100	004655-34-9	Methacrylic acid, isopropyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
21130	000080-62-6	Methacrylic acid, methyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
21190	000868-77-9	Methacrylic acid, monoester with ethyleneglycol	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
21280	002177-70-0	Methacrylic acid, phenyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
21340	002210-28-8	Methacrylic acid, propyl ester	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
[ <sup>F5</sup> 21370	010595-80-9	Methacrylic acid, 2-sulphoethyl ester	QMA = ND (DL = 0,02 mg/6 dm <sup>2</sup> )]
[ <sup>F2</sup> 21400	054276-35-6	Methacrylic acid, sulphopropyl ester	QMA = 0,05 mg/6 dm <sup>2</sup> ]
21460	000760-93-0	Methacrylic anhydride	[ <sup>F5</sup> SML(T) = 6 mg/kg ( <sup>37</sup> )]
21490	000126-98-7	Methacrylonitrile	SML = ND (DL = 0,020 mg/kg, analytical tolerance included)

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

21520	001561-92-8	Methallylsulphonic acid, sodium salt	SML = 5 mg/kg
21550	000067-56-1	Methanol	
21640	000078-79-5	2-Methyl-1,3-butadiene	QM = 1 mg/kg in FP or SML = ND (DL = 0,02 mg/kg, analytical tolerance included)
21730	000563-45-1	3-Methyl-1-butene	QMA = 0,006 mg/6 dm <sup>2</sup> . For use only in Polypropylene
21765	106246-33-7	4,4'-Methylenebis(3-chloro-2,6-diethylaniline)	QMA = 0,05 mg/6 dm <sup>2</sup>
21821	000505-65-7	1,4-(Methylenedioxy)butane	See '1,4-Butanediol formal'
21940	000924-42-5	N-Methylolacrylamide	SML = ND (DL = 0,01 mg/kg)
22150	000691-37-2	4-Methyl-1-pentene	[ <sup>F1</sup> SML = 0,05 mg/kg]
[ <sup>F5</sup> 22210	000098-83-9	alpha-Methylstyrene	SML = 0,05 mg/kg]
22331	025513-64-8	[ <sup>F1</sup> Mixture of (35-45 % w/w) 1,6-diamino-2,2,4-trimethylhexane and (55-65 % w/w) 1,6-diamino-2,4,4-trimethylhexane]	QMA = 5 mg/6 dm <sup>2</sup>
22332	[ <sup>F1</sup> —]	Mixture of (40 % w/w) 2,2,4-trimethylhexane-1,6-diisocyanate and (60 % w/w) 2,4,4-trimethylhexane-1,6-diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) ( <sup>26</sup> )
22350	000544-63-8	Myristic acid	
22360	001141-38-4	2,6-Naphthalenedicarboxylic acid	SML = 5 mg/kg
22390	000840-65-3	2,6-Naphthalenedicarboxylic acid, dimethyl ester	SML = 0,05 mg/kg

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

22420	003173-72-6	1,5-Naphthalene diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
22437	000126-30-7	Neopentylglycol	See '2,2-Dimethyl-1,3-propanediol'
22450	009004-70-0	Nitrocellulose	
22480	000143-08-8	1-Nonanol	
22550	000498-66-8	Norbornene	See 'Bicyclo[2.2.1]hept-2-ene'
22570	000112-96-9	Octadecyl isocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
22600	000111-87-5	1-Octanol	
22660	000111-66-0	1-Octene	SML = 15 mg/kg
22763	000112-80-1	Oleic acid	
[ <sup>F2</sup> 22775	000144-62-7	Oxalic acid	SML(T) = 6 mg/kg <sup>(29)</sup> ]
22778	007456-68-0	4,4'-Oxybis(benzenesulphonyl azide)	QMA = 0,05 mg/6 dm <sup>2</sup>
22780	000057-10-3	Palmitic acid	
22840	000115-77-5	Pentaerythritol	
22870	000071-41-0	1-Pentanol	
22900	000109-67-1	1-Pentene	SML = 5 mg/kg
[ <sup>F5</sup> 22932	001187-93-5	Perfluoromethyl perfluorovinyl ether	SML = 0,05 mg/kg. Only to be used for anti-stick coatings]
22937	001623-05-8	Perfluoropropylperfluoroether	SML = 0,05 mg/kg
22960	000108-95-2	Phenol	
23050	000108-45-2	1,3-Phenylenediamine	SML = ND (DL = 0,02 mg/kg, analytical tolerance included)
[ <sup>F2</sup> 23070	000102-39-6	(1,3-Phenylenedioxy)diacetic acid	QMA = 0,05 mg/6 dm <sup>2</sup> ]
23155	000075-44-5	Phosgene	See 'Carbonyl chloride'

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

23170	007664-38-2	Phosphoric acid	
23175	000122-52-1	Phosphorous acid, triethyl ester	QM = ND (DL = 1 mg/kg in FP)
23187		Phthalic acid	See 'Terephthalic acid'
23200	000088-99-3	o-Phthalic acid	
23230	000131-17-9	Phthalic acid, diallyl ester	SML = ND (DL = 0,01 mg/kg)
23380	000085-44-9	Phthalic anhydride	
23470	000080-56-8	alpha-Pinene	
23500	000127-91-3	beta-Pinene	
23547	009016-00-6 063148-62-9	Polydimethylsiloxane (Mw > 6 800)	In compliance with the specifications laid down in Annex V
23590	025322-68-3	Polyethyleneglycol	
23651	025322-69-4	Polypropyleneglycol	
23740	000057-55-6	1,2-Propanediol	
23770	000504-63-2	1,3-Propanediol	SML = 0,05 mg/kg
23800	000071-23-8	1-Propanol	
23830	000067-63-0	2-Propanol	
23860	000123-38-6	Propionaldehyde	
23890	000079-09-4	Propionic acid	
23920	000105-38-4	Propionic acid, vinyl ester	SML(T) = 6 mg/kg (superscript 2) (expressed as Acetaldehyde)
23950	000123-62-6	Propionic anhydride	
23980	000115-07-1	Propylene	
24010	000075-56-9	Propylene oxide	QM = 1 mg/kg in FP
24051	000120-80-9	Pyrocatechol	See '1,2-Dihydroxybenzene'
24057	000089-32-7	Pyromellitic anhydride	SML = 0,05 mg/kg (expressed as Pyromellitic acid)
24070	073138-82-6	Resin acids and Rosin acids	
24072	000108-46-3	Resorcinol	See '1,3-Dihydroxybenzene'
24073	000101-90-6	Resorcinol diglycidyl ether	QMA = 0,005 mg/6 dm <sup>2</sup> . Not for use in

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

			polymers contacting foods for which simulant D is laid down in Directive 85/572/EEC and for indirect food contact only, behind the PET layer.
24100	008050-09-7	Rosin	
24130	008050-09-7	Rosin gum	See 'Rosin'
24160	008052-10-6	Rosin tall oil	
24190	[ <sup>F4</sup> 008050-09-7]	Rosin wood	[ <sup>F5</sup> See 'Rosin' (Reference No 24100)]
24250	009006-04-6	Rubber, natural	
24270	000069-72-7	Salicylic acid	
24280	000111-20-6	Sebacic acid	
24430	002561-88-8	Sebacic anhydride	
24475	001313-82-2	Sodium sulphide	
24490	000050-70-4	Sorbitol	
24520	008001-22-7	Soybean oil	
24540	009005-25-8	Starch, edible	
24550	000057-11-4	Stearic acid	
24610	000100-42-5	Styrene	
24760	026914-43-2	Styrenesuphonic acid	SML = 0,05 mg/kg
24820	000110-15-6	Succinic acid	
24850	000108-30-5	Succinic anhydride	
24880	000057-50-1	Sucrose	
24887	006362-79-4	5-Sulphoisophthalic acid, monosodium salt	SML = 5 mg/kg
24888	003965-55-7	5-Sulphoisophthalic acid, monosodium salt, dimethyl ester	SML = 0,05 mg/kg
[ <sup>F5</sup> 24903	068425-17-2	Syrups, hydrolysed starch, hydrogenated	In compliance with the specifications laid down in Annex V]
24910	000100-21-0	Terephthalic acid	SML = 7,5 mg/kg

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

24940	000100-20-9	Terephthalic acid dichloride	SML(T) = 7,5 mg/kg (expressed as Terephthalic acid)
24970	000120-61-6	Terephthalic acid, dimethyl ester	
25080	001120-36-1	1-Tetradecene	SML = 0,05 mg/kg
25090	000112-60-7	Tetraethyleneglycol	
25120	000116-14-3	Tetrafluoroethylene	SML = 0,05 mg/kg
25150	000109-99-9	Tetrahydrofuran	SML = 0,6 mg/kg
25180	000102-60-3	N,N,N',N',-Tetrakis(2-hydroxypropyl)ethylenediamine	
25210	000584-84-9	2,4-Toluene diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
25240	000091-08-7	2,6-Toluene diisocyanate	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
25270	026747-90-0	2,4-Toluene diisocyanate dimer	QM(T) = 1 mg/kg (expressed as NCO) <sup>(26)</sup>
25360		Trialkyl(C5-C15)acetic acid, 2,3-epoxypropyl ester	QM = 1 mg/kg in FP (expressed as Epoxy group, Mw = 43)
25380	—	Trialkyl acetic acid (C7-C17), vinyl esters (= Vinyl versatate)	QMA = 0,05 mg/6 dm <sup>2</sup>
25385	000102-70-5	Triallylamine	In compliance with the specifications laid down in Annex V
25420	000108-78-1	2,4,6-Triamino-1,3,5-triazine	SML = 30 mg/kg
25450	026896-48-0	Tricyclodecanedimethanone	SML = 0,05 mg/kg
25510	000112-27-6	Triethyleneglycol	
[ <sup>F5</sup> 25540	000528-44-9	Trimellitic acid	SML(T) = 5 mg/kg <sup>(35)</sup>
25550	000552-30-7	Trimellitic anhydride	SML(T) = 5 mg/kg <sup>(35)</sup> (expressed as trimellitic acid)]



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

25600	000077-99-6	1,1,1-Trimethylolpropane	SML = 6 mg/kg
25840	003290-92-4	1,1,1-Trimethylolpropane trimethacrylate	SML = 0,05 mg/kg
25900	000110-88-3	Trioxane	SML = 0,05 mg/kg
25910	024800-44-0	Tripropyleneglycol	
25927	027955-94-8	1,1,1-Tris(4-hydroxyphenol)ethane	QM= 0,5 mg/kg in FP. For use only in polycarbonates
25960	000057-13-6	Urea	
26050	000075-01-4	Vinyl chloride	See Council Directive 78/142/EEC
26110	000075-35-4	Vinylidene chloride	QM = 5 mg/kg in FP or SML = ND (DL = 0,05 mg/kg)
26140	000075-38-7	Vinylidene fluoride	SML = 5 mg/kg
26155	001072-63-5	1-Vinylimidazole	QM = 5 mg/kg in FP
26170	003195-78-6	N-Vinyl-N-methylacetamide	QM = 2 mg/kg in FP
26320	002768-02-7	Vinyltrimethoxysilane	QM = 5 mg/kg in FP
26360	007732-18-5	Water	In compliance with Directive 98/83/EC

#### Textual Amendments

- F5** Inserted by [Commission Directive 2005/79/EC of 18 November 2005 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with food](#) (Text with EEA relevance).
- F6** Deleted by [Commission Directive 2005/79/EC of 18 November 2005 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with food](#) (Text with EEA relevance).

### Section B

LIST OF MONOMERS AND OTHER STARTING SUBSTANCES WHICH MAY CONTINUE TO BE USED PENDING A DECISION ON INCLUSION IN SECTION A

Ref. No	CAS No	Name	Restrictions and/or specifications
(1)	(2)	(3)	(4)

[<sup>F3</sup>

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

F3			
F3			
F3]			
[F6]			
13050	000528-44-9	1,2,4-Benzenetricarboxylic acid	See 'Trimellitic acid'
[F6]			
[F3]			
15730	000077-73-6	Dicyclopentadiene	
[F3			
F3]			
18370	000592-45-0	1,4-Hexadiene	
[F3]			
[F6]			
[F3]			
21970	000923-02-4	N-Methylmethacrylamide	
[F6			
F6			
F6]			
26230	000088-12-0	Vinylpyrrolidone	

### ANNEX III

#### INCOMPLETE LIST OF ADDITIVES WHICH MAY BE USED IN THE MANUFACTURE OF PLASTIC MATERIALS AND ARTICLES GENERAL INTRODUCTION

[F1]. This Annex contains the list of:

- (a) substances which are incorporated into plastics to achieve a technical effect in the finished product, including 'polymeric additives'. They are intended to be present in the finished articles;
- (b) substances used to provide a suitable medium in which polymerisation occurs.

For the purposes of this Annex, the substances referred to in (a) and (b) are hereinafter referred to as 'additives'.

For the purpose of this Annex, 'Polymeric additives' means any polymer and/or prepolymer and/or oligomer which may be added to plastics in order to achieve a technical effect but which cannot be used in absence of other polymers as the main structural component of finished materials and articles. It includes also substances which may be added to the medium in which polymerisation occurs.

The list does not include:

- (a) the substances which directly influence the formation of polymers;
- (b) colorants;
- (c) solvents.]

[<sup>F42</sup>2. The following substances are not included even if they are intentionally used and are authorised:

- (a) salts (including double salts and acid salts) of aluminium, ammonium, calcium, iron, magnesium, potassium and sodium of authorised acids, phenols or alcohols. However, names containing '... acid(s), salts' appear in the lists, if the corresponding free acid(s) is (are) not mentioned;
- (b) salts (including double salts and acid salts) of zinc of authorised acids, phenols or alcohols. For these salts a Group SML = 25 mg/kg (expressed as Zn) apply. The same restriction for Zn applies to:
  - (i) substances whose name contains '... acid(s), salts' which appear in the lists, if the corresponding free acid(s) is (are) not mentioned,
  - (ii) substances referred to in note 38 of Annex VI.]

3. The list does not include the following substances although they may be present:

- (a) substances which could be present in the finished product such as:
  - impurities in the substances used,
  - reaction intermediates,
  - decomposition products;
- (b) mixtures of the authorised substances.

The materials and articles which contain the substances indicated in (a) and (b) shall comply with the requirements stated in article 2 of Directive 89/109/EEC.

4. Substances shall be of good technical quality as regards the purity criteria.

5. The list contains the following information:

- column 1 (Ref. No): the EEC packaging material reference number of the substances on the list,
- column 2 (CAS No): the CAS (Chemical Abstracts Service) registry number,
- column 3 (Name): the chemical name,
- column 4 (Restrictions and/or specifications). These may include:
  - specific migration limit (SML),
  - maximum permitted quantity of the substance in the finished material or article (QM),

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

- maximum permitted quantity of the substance in the finished material or article expressed as mg per 6 dm<sup>2</sup> of the surface in contact with foodstuffs (QMA),
  - any other restriction specifically laid down,
  - any type of specification related to the substance or polymer.
6. If a substance appearing on the list as an individual compound is also covered by a generic term, the restrictions applying to this substance shall be those indicated for the individual compound.
7. Where there is any inconsistency between the CAS number and the chemical name, the chemical name shall take precedence over the CAS number. If there is an inconsistency between the CAS number reported in EINECS and the CAS registry, the CAS number in the CAS registry shall apply.

### Section A

#### INCOMPLETE LIST OF ADDITIVES FULLY HARMONISED AT COMMUNITY LEVEL

Ref. No	CAS No	Name	Restrictions and/or specifications
(1)	(2)	(3)	(4)
30000	000064-19-7	Acetic acid	
30045	000123-86-4	Acetic acid, butyl ester	
30080	004180-12-5	Acetic acid, copper salt	[ <sup>F4</sup> SML(T) = 5 mg/kg ( <sup>7</sup> ) (expressed as Copper)]
30140	000141-78-6	Acetic acid, ethyl ester	
30280	000108-24-7	Acetic anhydride	
30295	000067-64-1	Acetone	
[ <sup>F5</sup> 30340	330198-91-9	12-(Acetoxy)stearic acid, 2,3-bis(acetoxy)propyl ester	]
30370	—	Acetylacetic acid, salts	
[ <sup>F6</sup> ]			
[ <sup>F5</sup> 30401	—	Acetylated mono- and diglycerides of fatty acids	]
30610	—	Acids, C <sub>2</sub> -C <sub>24</sub> , aliphatic, linear, monocarboxylic from	

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

		natural oils and fats, and their mono-, di- and triglycerol esters (branched fatty acids at naturally occurring levels are included)	
30612	—	Acids, C <sub>2</sub> -C <sub>24</sub> , aliphatic, linear, monocarboxylic, synthetic and their mono-, di- and triglycerol esters	
30960	—	Acids, aliph., monocarb. (C <sub>6</sub> -C <sub>22</sub> ), esters with polyglycerol	
31328	—	Acids, fatty, from animal or vegetable food fats and oils	
31530	123968-25-2	Acrylic acid, 2,4-di-tert-pentyl-6-(1-(3,5-di-tert-pentyl-2-hydroxyphenyl)ethyl)phenyl ester	SML = 5 mg/kg
[ <sup>F5</sup> 31542	174254-23-0	Acrylic acid, methyl ester, telomer with 1-dodecanethiol, C <sub>16</sub> -C <sub>18</sub> alkyl esters	QM = 0,5 % (w/w) in FP]
31730	000124-04-9	Adipic acid	
33120	—	Alcohols, aliph, monoh., sat., linear, primary (C <sub>4</sub> -C <sub>24</sub> )	
33350	009005-32-7	Alginic acid	
33801	—	n-Alkyl(C <sub>10</sub> -C <sub>13</sub> )benzenesulphonic acid	SML = 30 mg/kg
34240	—	Alkyl(C <sub>10</sub> -C <sub>20</sub> )sulphonic acid, esters with phenols	SML = 6 mg/kg. Authorised until 1 January 2002
34281	—	Alkyl(C <sub>8</sub> -C <sub>22</sub> )sulphuric acids, linear, primary with an even number of carbon atoms	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

34475	—	Aluminum calcium hydroxide phosphite, hydrate	
34480	—	Aluminium fibers, flakes and powders	
34560	021645-51-2	Aluminium hydroxide	
34690	011097-59-9	Aluminium magnesium carbonate hydroxide	
34720	001344-28-1	Aluminium oxide	
[ <sup>F2</sup> 34850	143925-92-2	Amines, bis(hydrogenated tallow alkyl) oxidised	QM = For use only: (a) in polyolefines at 0,1 % (w/w) but not in LDPE when it is in contact with foods for which the Directive 85/572/EEC establishes a reduction factor less than 3; (b) in PETat 0,25 % (w/w) in contact with foods other of those for which the simulat D is laid down in Directive 85/572/EEC 85/572/EEC
34895	000088-68-6	2-Aminobenzamide	SML = 0,05 mg/kg. To be used only for PET for water and beverages]
35120	013560-49-1	3-Aminocrotonic acid, diester with thiobis (2-hydroxyethyl) ether	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

35160	006642-31-5	6-Amino-1,3-dimethyluracil	SML = 5 mg/kg
35170	000141-43-5	2-Aminoethanol	SML = 0,05 mg/kg. Not for use in polymers contacting foods for which simulant D is laid down in Directive 85/572/EEC and for indirect food contact only, behind the PET layer
35284	000111-41-1	N-(2-aminoethyl)ethanolamine	SML = 0,05 mg/kg. Not for use in polymers contacting foods for which simulant D is laid down in Directive 85/572/EEC and for indirect food contact only, behind the PET layer.
35320	007664-41-7	Ammonia	
35440	001214-97-9	Ammonium bromide	
35600	001336-21-6	Ammonium hydroxide	
35840	000506-30-9	Arachidic acid	
35845	007771-44-0	Arachidonic acid	
36000	000050-81-7	Ascorbic acid	
36080	000137-66-6	Ascorbyl palmitate	
36160	010605-09-1	Ascorbyl stearate	
36640	000123-77-3	Azodicarbonamide	[ <sup>F7</sup> For use only as blowing agent. Use prohibited as from 2 August 2005.]
36840	012007-55-5	Barium tetraborate	SML(T) = 1 mg/kg expressed as Barium ( <sup>12</sup> ) and SML(T) = 6 mg/kg ( <sup>23</sup> ) expressed as Boron) without prejudice to the provisions of Directive 98/83/EC on water for human

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

			consumption (OJ L330, 5.12.1998, p. 32).
36880	008012-89-3	Beeswax	
36960	003061-75-4	Behenamamide	
37040	000112-85-6	Behenic acid	
37280	001302-78-9	Bentonite	
37360	000100-52-7	Benzaldehyde	In compliance with note 9 in Annex VI
37600	000065-85-0	Benzoic acid	
37680	000136-60-7	Benzoic acid, butyl ester	
37840	000093-89-0	Benzoic acid, ethyl ester	
38080	000093-58-3	Benzoic acid, methyl ester	
38160	002315-68-6	Benzoic acid, propyl ester	
[ <sup>F6</sup> ]			
38510	136504-96-6	1,2-Bis(3-aminopropyl)ethylenediamine, polymer with N-butyl-2,2,6,6-tetramethyl-4-piperidinamine and 2,4,6-trichloro-1,3,5-triazine	SML = 5 mg/kg
38515	001533-45-5	4,4'-Bis(2-benzoxazolyl)stilbene	SML = 0,05 mg/kg ( <sup>1</sup> )
38810	080693-00-1	Bis(2,6-di-tert-butyl-4-methylphenyl)pentaerythritol diphosphite	SML = 5 mg/kg (sum of phosphite and phosphate)
38840	154862-43-8	Bis(2,4-dicumylphenyl)pentaerythritol diphosphite	SML = 5 mg/kg (as sum of the substance itself, its oxidised form bis(2,4-dicumylphenyl)pentaerythritol-phosphate and its hydrolysis product (2,4-dicumylphenol)).
38879	135861-56-2	Bis(3,4-dimethylbenzylidene)sorbitol	



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

38950	079072-96-1	Bis(4-ethylbenzylidene)sorbitol	
39200	006200-40-4	Bis(2-hydroxyethyl)-2-hydroxypropyl-3-(dodecyloxy)methylammonium chloride	SML = 1,8 mg/kg
[ <sup>F2</sup> 39680	000080-05-7	2,2-Bis(4-hydroxyphenyl)propane <sup>(28)</sup> ]	SML(T) = 0,6 mg/kg
39815	182121-12-6	9,9-Bis(methoxymethyl)fluorene	QMA = 0,05 mg/6 dm <sup>2</sup>
39890	087826-41-3 069158-41-4 054686-97-4 081541-12-0	Bis(methylbenzylidene)sorbitol	
39925	129228-21-3	3,3-Bis(methoxymethyl)-2,5-dimethylhexane	SML = 0,05 mg/kg
40120	068951-50-8	Bis(polyethyleneglycol)hydroxypropylphosphonate	SML = 0,6 mg/kg
40320	010043-35-3	Boric acid	SML(T) = 6 mg/kg <sup>(23)</sup> (expressed as Boron) without prejudice to the provisions of Directive 98/83/EC on water for human consumption (OJ L 330, 5.12.1998, p.32).
40400	010043-11-5	Boron nitride	
40570	000106-97-8	Butane	
40580	000110-63-4	1,4-Butanediol	[ <sup>F4</sup> SML(T) = 5 mg/kg <sup>(24)</sup> ]
41040	005743-36-2	Calcium butyrate	
41120	010043-52-4	Calcium chloride	
41280	001305-62-0	Calcium hydroxide	
41520	001305-78-8	Calcium oxide	
41600	012004-14-7 037293-22-4	Calcium sulfoaluminate	
41680	000076-22-2	Camphor	In compliance with note 9 in Annex VI
41760	008006-44-8	Candelilla wax	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

41840	000105-60-2	Caprolactam	SML(T) = 15 mg/kg <sup>(5)</sup>
41960	000124-07-2	Caprylic acid	
42160	000124-38-9	Carbon dioxide	
42320	007492-68-4	Carbonic acid, copper salt	[ <sup>F4</sup> SML(T) = 5 mg/kg <sup>(7)</sup> (expressed as Copper)]
42500	—	Carbonic acid, salts	
42640	009000-11-7	Carboxymethylcellulose	
42720	008015-86-9	Carnauba wax	
42800	009000-71-9	Casein	
[ <sup>F2</sup> 42880	008001-79-4	Castor oil	]
42960	064147-40-6	Castor oil, dehydrated	
43200	—	Castor oil, mono- and diglycerides	
43280	009004-34-6	Cellulose	
43300	009004-36-8	Cellulose acetate butyrate	
43360	068442-85-3	Cellulose, regenerated	
43440	008001-75-0	Ceresin	
[ <sup>F5</sup> 43480	064365-11-3	Charcoal, activated	In compliance with the specifications laid down in Annex V, Part B]
43515	—	Chlorides of choline esters of coconut oil fatty acids	QMA = 0,9 mg/6 dm <sup>2</sup>
44160	000077-92-9	Citric acid	
44640	000077-93-0	Citric acid, triethyl ester	
45195	007787-70-4	Copper bromide	[ <sup>F4</sup> SML(T) = 5 mg/kg <sup>(7)</sup> (expressed as Copper)]
45200	001335-23-5	Copper iodide	[ <sup>F4</sup> SML(T) = 5 mg/kg <sup>(7)</sup> (expressed as Copper)]
45280	—	Cotton fibers	

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

45450	068610-51-5	p-Cresol-dicyclopentadiene-isobutylene, copolymer	[ <sup>F1</sup> SML = 5 mg/kg]
45560	014464-46-1	Cristobalite	
[ <sup>F2</sup> 45600	003724-65-0	Crotonic acid	QMA(T) = 0,05 mg/6 dm <sup>2</sup> ( <sup>33</sup> )
45640	005232-99-5	2-Cyano-3,3-diphenylacrylic acid, ethyl ester	SML = 0,05 mg/kg]
45760	000108-91-8	Cyclohexylamine	
45920	009000-16-2	Dammar	
45940	000334-48-5	n-Decanoic acid	
46070	010016-20-3	alpha-Dextrin	
46080	007585-39-9	beta-Dextrin	
46375	061790-53-2	Diatomaceous earth	
46380	068855-54-9	Diatomaceous earth, soda ash flux-calcined	
46480	032647-67-9	Dibenzylidene sorbitol	
[ <sup>F2</sup> 46700	—	5,7-di-tert-Butyl-3-(3,4- and 2,3-dimethylphenyl)-3H-benzofuran-2-one containing: a) 5,7-di-tert-butyl-3-(3,4-dimethylphenyl)-3H-benzofuran-2-one (80 to 100 % w/w) and b) 5,7-di-tert-butyl-3-(2,3-dimethylphenyl)-3H-benzofuran-2-one (0 to 20 % w/w)	SML = 5 mg/kg
46720	004130-42-1	2,6-Di-tert-butyl-4-ethylphenol	QMA = 4,8 mg/6 dm <sup>2</sup>
46790	004221-80-1	3,5-Di-tert-butyl-4-hydroxybenzoic acid, 2,4-di-tert-butylphenyl ester	
46800	067845-93-6	3,5-Di-tert-butyl-4-hydroxybenzoic acid, hexadecyl ester	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

46870	003135-18-0	3,5-Di-tert-butyl-4-hydroxybenzylphosphonic acid, dioctadecyl ester	
46880	065140-91-2	3,5-Di-tert-butyl-4-hydroxybenzylphosphonic acid, monoethyl ester, calcium salt	SML = 6 mg/kg
47210	026427-07-6	Dibutylthiostannic acid polymer [= Thiobis(butyl-tin sulphide), polymer]	In compliance with the specifications laid down in Annex V.
47440	000461-58-5	Dicyanodiamide	
47540	027458-90-8	Di-tert-dodecyl disulphide	SML = 0,05 mg/kg
47680	000111-46-6	Diethyleneglycol	SML(T) = 30 mg/kg <sup>(3)</sup>
48460	000075-37-6	1,1-Difluoroethane	
48620	000123-31-9	1,4-Dihydroxybenzene	SML = 0,6 mg/kg
48720	000611-99-4	4,4'-Dihydroxybenzophenone	SML(T) = 6 mg/kg <sup>(15)</sup>
49485	134701-20-5	2,4-Dimethyl-6-(1-methylpentadecyl)phenol	SML = 1 mg/kg
49540	000067-68-5	Dimethyl sulphoxide	
51200	000126-58-9	Dipentaerythritol	
51700	147315-50-2	2-(4,6-Diphenyl-1,3,5-triazin-2-yl)-5-(hexyloxy)phenol	SML = 0,05 mg/kg
51760	025265-71-8 000110-98-5	Dipropylenglycol	
52640	016389-88-1	Dolomite	
52645	010436-08-5	cis-11-Eicosenamide	
52720	000112-84-5	Erucamide	
52730	000112-86-7	Erucic acid	
52800	000064-17-5	Ethanol	
53270	037205-99-5	Ethylcarboxymethylcellulose	
53280	009004-57-3	Ethylcellulose	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

53360	000110-31-6	N,N'-Ethylenebisoleamide	
53440	005518-18-3	N,N'-Ethylenebispalmitamide	
53520	000110-30-5	N,N'-Ethylenebisstearamide	
53600	000060-00-4	Ethylenediaminetetraacetic acid	
53610	054453-03-1	Ethylenediaminetetraacetic acid, copper salt	SML(T) = 5 mg/kg <sup>(7)</sup> (expressed as Copper)]
53650	000107-21-1	Ethyleneglycol	SML(T) = 30 mg/kg <sup>(3)</sup>
54005	005136-44-7	Ethylene-N-palmitamide-N'-stearamide	
54260	009004-58-4	Ethylhydroxyethylcellulose	
54270	—	Ethylhydroxymethylcellulose	
54280	—	Ethylhydroxypropylcellulose	
54300	118337-09-0	2,2'-Ethylidenebis(4,6-di-tert-butylphenyl) fluorophosphonite	SML = 6 mg/kg
54450	—	Fats and oils, from animal or vegetable food sources	
54480	—	Fats and oils, hydrogenated, from animal or vegetable food sources	
54930	025359-91-5	Formaldehyde-1-naphthol, copolymer [=poly(1-hydroxynaphthylmethane)]	SML = 0,05 mg/kg
55040	000064-18-6	Formic acid	
55120	000110-17-8	Fumaric acid	
55190	029204-02-2	Gadoleic acid	
55440	009000-70-8	Gelatin	
55520	—	Glass fibers	
55600	—	Glass microballs	
55680	000110-94-1	Glutaric acid	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

55920	000056-81-5	Glycerol	
56020	099880-64-5	Glycerol dibehenate	
56360	—	Glycerol, esters with acetic acid	
56486	—	Glycerol, esters with acids, aliph., sat., linear, with an even number of carbon atoms (C <sub>14</sub> -C <sub>18</sub> ) and with acids, aliph., unsat., linear, with an even number of carbon atoms (C <sub>16</sub> -C <sub>18</sub> )	
56487	—	Glycerol, esters with butyric acid	
56490	—	Glycerol, esters with erucic acid	
56495	—	Glycerol, esters with 12-hydroxystearic acid	
56500	—	Glycerol, esters with lauric acid	
56510	—	Glycerol, esters with linoleic acid	
56520	—	Glycerol, esters with myristic acid	
[ <sup>F2</sup> 56535	—	Glycerol, esters with nonanoic acid	]
56540	—	Glycerol, esters with oleic acid	
56550	—	Glycerol, esters with palmitic acid	
[ <sup>F3</sup> ]			
56570	—	Glycerol, esters with propionic acid	
56580	—	Glycerol, esters with ricinoleic acid	
56585	—	Glycerol, esters with stearic acid	
56610	030233-64-8	Glycerol monobehenate	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

56720	026402-23-3	Glycerol monoheptanoate	
56800	030899-62-8	Glycerol monolaurate diacetate	
56880	026402-26-6	Glycerol monooctanoate	
57040	—	Glycerol monooleate, ester with ascorbic acid	
57120	—	Glycerol monooleate, ester with citric acid	
57200	—	Glycerol monopalmitate, ester with ascorbic acid	
57280	—	Glycerol monopalmitate, ester with citric acid	
57600	—	Glycerol monostearate, ester with ascorbic acid	
57680	—	Glycerol monostearate, ester with citric acid	
57800	018641-57-1	Glycerol tribehenate	
57920	000620-67-7	Glycerol triheptanoate	
58300	—	Glycine, salts	
58320	007782-42-5	Graphite	
58400	009000-30-0	Guar gum	
58480	009000-01-5	Gum arabic	
58720	000111-14-8	Heptanoic acid	
[ <sup>F2</sup> 59280	000100-97-0	Hexamethylenetetramine	SML(T) = 15 mg/kg ( <sup>22</sup> ) (expressed as Formaldehyde)]
59360	000142-62-1	Hexanoic acid	
59760	019569-21-2	Huntite	
59990	007647-01-0	Hydrochloric acid	
60030	012072-90-1	Hydromagnesite	
60080	012304-65-3	Hydrotalcite	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

60160	000120-47-8	4-Hydroxybenzoic acid, ethyl ester	
60180	004191-73-5	4-Hydroxybenzoic acid, isopropyl ester	
60200	000099-76-3	4-Hydroxybenzoic acid, methyl ester	
60240	000094-13-3	4-Hydroxybenzoic acid, propyl ester	
60480	003864-99-1	2-(2'-Hydroxy-3,5'-di-tert-butylphenyl)-5-chlorobenzotriazole	SML(T) = 30 mg/kg ( <sup>19</sup> )
60560	009004-62-0	Hydroxyethylcellulose	
60880	009032-42-2	Hydroxyethylmethylcellulose	
61120	009005-27-0	Hydroxyethyl starch	
61390	037353-59-6	Hydroxymethylcellulose	
61680	009004-64-2	Hydroxypropylcellulose	
61800	009049-76-7	Hydroxypropyl starch	
61840	000106-14-9	12-Hydroxystearic acid	
62140	006303-21-5	Hypophosphorous acid	
62240	001332-37-2	Iron oxide	
[ <sup>F5</sup> 62245	012751-22-3	Iron phosphide	For PET polymers and copolymers only]
62450	000078-78-4	Isopentane	
62640	008001-39-6	Japan wax	
62720	001332-58-7	Kaolin	
62800	—	Kaolin, calcined	
62960	000050-21-5	Lactic acid	
63040	000138-22-7	Lactic acid, butyl ester	
63280	000143-07-7	Lauric acid	
63760	008002-43-5	Lecithin	
63840	000123-76-2	Levulinic acid	
63920	000557-59-5	Lignoceric acid	
64015	000060-33-3	Linoleic acid	
64150	028290-79-1	Linolenic acid	



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

64500	—	Lysine, salts	
64640	001309-42-8	Magnesium hydroxide	
64720	001309-48-4	Magnesium oxide	
64800	00110-16-7	Maleic acid	SML(T) = 30 mg/kg <sup>(4)</sup>
[ <sup>F5</sup> 64990	025736-61-2	Maleic anhydride-styrene, copolymer, sodium salt	In compliance with specifications laid down in Annex V]
65020	006915-15-7	Malic acid	
65040	000141-82-2	Malonic acid	
65520	000087-78-5	Mannitol	
65920	066822-60-4	N-Methacryloyloxyethyl-N,N-dimethyl-N-carboxymethylammonium chloride, sodium salt -octadecyl methacrylate-ethyl methacrylate-cyclohexyl methacrylate-N-vinyl-2-pyrrolidone, copolymers	
66200	037206-01-2	Methylcarboxymethylcellulose	
66240	009004-67-5	Methylcellulose	
66560	004066-02-8	2,2'-Methylenebis(4-methyl-6-cyclohexylphenol)	SML(T) = 3 mg/kg <sup>(6)</sup>
66580	000077-62-3	2,2'-Methylenebis(4-methyl-6-(1-methylcyclohexyl)phenol)	SML(T) = 3 mg/kg <sup>(6)</sup>
66640	009004-59-5	Methylethylcellulose	
66695	—	Methylhydroxymethylcellulose	
66700	009004-65-3	Methylhydroxypropylcellulose	
66755	002682-20-4	2-Methyl-4-isothiazolin-3-one	SML = ND (DL = 0,02 mg/kg, analytical tolerance included)
[ <sup>F5</sup> 66905	000872-50-4	N-Methylpyrrolidone	
66930	068554-70-1	Methylsilsesquioxane	Residual monomer in methylsilsesquioxane:

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

			< 1 mg methyltrimethoxysilane/kg of methylsilsesquioxane]
67120	012001-26-2	Mica	
[ <sup>F5</sup> 67155	—	Mixture of 4-(2-Benzoxazolyl)-4'-(5-methyl-2-benzoxazolyl)stilbene, 4,4'-bis(2-benzoxazolyl) stilbene and 4,4'-bis(5-methyl-2-benzoxazolyl)stilbene)	Not more than 0,05 % w/w (quantity of substance used/ quantity of the formulation). In compliance with the specifications laid down in Annex V]
[ <sup>F3</sup>			
67180	—	Mixture of (50 % w/w) phthalic acid, n-decyl n-octyl ester, (25 % w/w) phthalic acid di-n-decyl ester, and (25 % w/w) phthalic acid di-n-decyl ester, and (25 % w/w) phthalic acid di-n-octyl ester	SML = 5 mg/kg ( <sup>1</sup> )
67200	001317-33-5	Molybdenum disulphide	
67840	—	Montanic acids and/or their esters with ethyleneglycol and/or with 1,3-butanediol and/or with glycerol	
67850	008002-53-7	Montan wax	
67891	000544-63-8	Myristic acid	
68040	003333-62-8	7-[2H-Naphtho-(1,2-D)triazol-2-yl]-3-phenylcoumarin	
[ <sup>F2</sup> 68078	027253-31-2	Neodecanoic acid, cobalt salt	SML(T) = 0,05 mg/kg (expressed as Neodecanoic acid) and SML(T) = 0,05 mg/kg ( <sup>14</sup> ) (expressed as Cobalt). Not for use in polymers contacting foods for which simulant D is laid

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

			down in Directive 85/572/EEC.]
68125	037244-96-5	Nepheline syenite	
68145	080410-33-9	2,2',2''-Nitrilo(triethyl tris(3,3',5,5'-tetra-tert-butyl-1,1'-bi-phenyl-2,2'-diyl)phosphite)	SML =5 mg/kg (sum of phosphite and phosphate)
68960	000301-02-0	Oleamide	
69040	000112-80-1	Oleic acid	
69760	000143-28-2	Oleyl alcohol	
[ <sup>F2</sup> 69920	000144-62-7	Oxalic acid	SML(T) = 6 mg/kg ( <sup>29</sup> )]
70000	070331-94-1	2,2'-Oxamidobis[ethyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate]	
70240	012198-93-5	Ozokerite	
70400	000057-10-3	Palmitic acid	
71020	000373-49-9	Palmitoleic acid	
71440	009000-69-5	Pectin	
71600	000115-77-5	Pentaerythritol	
71635	025151-96-6	Pentaerythritol dioleate	SML = 0,05 mg/kg. Not for use in polymers contacting foods for which simulant D is laid down in Directive 85/572/EEC
71670	178671-58-4	Pentaerythritol tetrakis (2-cyano-3,3-diphenylacrylate)	SML = 0,05 mg/kg
71680	006683-19-8	Pentaerythritol tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate]	
71720	000109-66-0	Pentane	
72640	007664-38-2	Phosphoric acid	
73160	—	Phosphoric acid, mono- and di-n-alkyl (C <sub>16</sub> and C <sub>18</sub> ) esters	SML = 0,05 mg/kg

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

73720	000115-96-8	Phosphoric acid, trichloroethyl ester	SML = ND (DL = 0,02 mg/kg, analytical tolerance included)
74010	145650-60-8	Phosphorous acid, bis(2,4-di-tert-butyl-6-methylphenyl) ethyl ester	SML = 5 mg/kg (sum of phosphite and phosphate)
74240	031570-04-4	Phosphorous acid, tris(2,4-di-tert-butylphenyl)ester	
74480	000088-99-3	o-Phthalic acid	
76320	000085-44-9	Phthalic anhydride	
[ <sup>F5</sup> 76415]	019455-79-9	Pimelic acid, calcium salt	]
76721	009016-00-6 063148-62-9	Polydimethylsiloxane (Mw > 6800)	In compliance with the specifications laid down in Annex V
76730	—	Polydimethylsiloxane, gamma-hydroxypropylated	SML = 6 mg/kg
[ <sup>F5</sup> 76815]	—	Polyester of adipic acid with glycerol or pentaerythritol, esters with even numbered, unbranched C <sub>12</sub> -C <sub>22</sub> fatty acids	In compliance with the specifications laid down in Annex V
76845	031831-53-5	Polyester of 1,4-butanediol with caprolactone	In compliance with the specifications laid down in Annex V]
[ <sup>F3</sup> ]			
[ <sup>F2</sup> 76866]	—	Polyesters of 1,2-propanediol and/or 1,3- and/or 1,4-butanediol and/or polypropyleneglycol with adipic acid, which may be end-capped with acetic acid or fatty acids C <sub>12</sub> -C <sub>18</sub> or n-octanol and/or n-decanol	SML = 30 mg/kg]
76960	025322-68-3	Polyethyleneglycol	

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

[ <sup>F5</sup> 77370	070142-34-6	Polyethyleneglycol-30 dipolyhydroxystearate	] ]
77600	061788-85-0	Polyethyleneglycol ester of hydrogenated castor oil	
77702	—	Polyethyleneglycol esters of aliph. monocarb. acids (C <sub>6</sub> -C <sub>22</sub> ) and their ammonium and sodium sulphates	
77895	068439-49-6	Polyethyleneglycol (EO = 2-6) monoalkyl (C <sub>16</sub> -C <sub>18</sub> ) ether	[ <sup>F1</sup> SML = 0,05 mg/ kg and in compliance with the specifications laid down in Annex V]
79040	009005-64-5	Polyethyleneglycol sorbitan monolaurate	
79120	009005-65-6	Polyethyleneglycol sorbitan monooleate	
79200	009005-66-7	Polyethyleneglycol sorbitan monopalmitate	
79280	009005-67-8	Polyethyleneglycol sorbitan monostearate	
79360	009005-70-3	Polyethyleneglycol sorbitan trioleate	
79440	009005-71-4	Polyethyleneglycol sorbitan tristearate	
[ <sup>F5</sup> 79600	009046-01-9	Polyethyleneglycol tridecyl ether phosphate	SML = 5 mg/kg. For materials and articles intended for contact with aqueous foods only. In compliance with the specification laid down in Annex V
80000	009002-88-4	Polyethylene wax	] ]
80240	029894-35-7	Polyglycerol ricinoleate	
80640	—	Polyoxyalkyl (C <sub>2</sub> -C <sub>4</sub> ) dimethylpolysiloxane	
80720	008017-16-1	Polyphosphoric acids	
80800	025322-69-4	Polypropyleneglycol	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

[ <sup>F5</sup> 81060	009003-07-0	Polypropylene wax	]
81220	192268-64-7	Poly-[[6-[N-(2,2,6,6-tetramethyl-4-piperidiny)-n-butylamino]-1,3,5-triazine-2,4-diyl][(2,2,6,6-tetramethyl-4-piperidiny)imino]-1,6-hexanediy][(2,2,6,6-tetramethyl-4-piperidiny)imino]]-alpha-[N,N,N',N'-tetrabutyl-N''-(2,2,6,6-tetramethyl-4-piperidiny)-N''-[6-(2,2,6,6-tetramethyl-4-piperidiny)amino]-hexyl]-[1,3,5-triazine-2,4,6-triazine]-omega-N,N,N',N'-tetrabutyl-1,3,5-triazine-2,4-diamine]	SML = 5 mg/kg
81515	087189-25-1	Poly(zinc glycerolate)	[ <sup>F5</sup> SML(T) = 25 mg/kg ( <sup>38</sup> ) (as Zinc)]
81520	007758-02-3	Potassium bromide	
81600	001310-58-3	Potassium hydroxide	
81760	—	Powders, flakes and fibres of brass, bronze, copper, stainless steel, tin and alloys of copper, tin and iron	[ <sup>F4</sup> SML(T) = 5 mg/kg ( <sup>7</sup> ) (expressed as Copper)]
81840	000057-55-6	1,2-Propanediol	
81882	000067-63-0	2-Propanol	
82000	000079-09-4	Propionic acid	
82080	009005-37-2	1,2-Propyleneglycol alginate	
82240	022788-19-8	1,2-Propyleneglycol dilaurate	
82400	000105-62-4	1,2-Propyleneglycol dioleate	

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

82560	033587-20-1	1,2-Propyleneglycol dipalmitate	
82720	006182-11-2	1,2-Propyleneglycol distearate	
82800	027194-74-7	1,2-Propyleneglycol monolaurate	
82960	001330-80-9	1,2-Propyleneglycol monooleate	
83120	029013-28-3	1,2-Propyleneglycol monopalmitate	
83300	001323-39-3	1,2-Propyleneglycol monostearate	
83320	—	Propylhydroxyethylcellulose	
83325	—	Propylhydroxymethylcellulose	
83330	—	Propylhydroxypropylcellulose	
83440	002466-09-3	Pyrophosphoric acid	
83455	013445-56-2	Pyrophosphorous acid	
83460	012269-78-2	Pyrophyllite	
83470	014808-60-7	Quartz	
83599	068442-12-6	Reaction products of oleic acid, 2-mercaptoethyl ester, with dichlorodimethyltin, sodium sulphide and trichloromethyltin	SML(T) = 0,18 mg/kg ( <sup>16</sup> ) (expressed as Tin)
83610	073138-82-6	Resin acids and Rosin acids	
83840	008050-09-7	Rosin	
84000	008050-31-5	Rosin, ester with glycerol	
84080	008050-26-8	Rosin, ester with pentaerythritol	
84210	065997-06-0	Rosin, hydrogenated	
84240	065997-13-9	Rosin, hydrogenated, ester with glycerol	
84320	008050-15-5	Rosin, hydrogenated, ester with methanol	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

84400	064365-17-9	Rosin, hydrogenated, ester with pentaerythritol	
84560	009006-04-6	Rubber, natural	
84640	000069-72-7	Salicylic acid	
85360	000109-43-3	Sebacic acid, dibutyl ester	
[ <sup>F3</sup> ]			
[ <sup>F2</sup> 85601	—	Silicates, natural (with the exception of asbestos)	]
85610	—	Silicates, natural, silanated (with the exception of asbestos)	
85680	001343-98-2	Silicic acid	
85840	053320-86-8	Silicic acid, lithium magnesium sodium salt	SML(T) = 0,6 mg/kg ( <sup>8</sup> ) (expressed as Lithium)
86000	—	Silicic acid, silylated	
86160	000409-21-2	Silicon carbide	
86240	007631-86-9	Silicon dioxide	
86285	—	Silicon dioxide, silanated	
86560	007647-15-6	Sodium bromide	
86720	001310-73-2	Sodium hydroxide	
87040	001330-43-4	Sodium tetraborate	SML(T) = 6 mg/kg ( <sup>23</sup> ) (expressed as Boron) without prejudice to the provisions of Directive 98/83/EC on water for human consumption (OJ L 330, 5.12.1998, p.32).
87200	000110-44-1	Sorbic acid	
87280	029116-98-1	Sorbitan dioleate	
87520	062568-11-0	Sorbitan monobehenate	
87600	001338-39-2	Sorbitan monolaurate	
87680	001338-43-8	Sorbitan monooleate	



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

87760	026266-57-9	Sorbitan monopalmitate	
87840	001338-41-6	Sorbitan monostearate	
87920	061752-68-9	Sorbitan tetrastearate	
88080	026266-58-0	Sorbitan trioleate	
88160	054140-20-4	Sorbitan tripalmitate	
88240	026658-19-5	Sorbitan tristearate	
88320	000050-70-4	Sorbitol	
88600	026836-47-5	Sorbitol monostearate	
88640	008013-07-8	Soybean oil, epoxidised	[ <sup>F4</sup> SML = 60 mg/kg. However in the case of PVC gaskets used to seal glass jars containing infant formulae and follow-on formulae as defined by Commission Directive 91/321/EEC or containing processed cereal-based foods and baby foods for infants and young children as defined by Directive 96/5/EC, the SML is lowered to 30 mg/kg]
88800	009005-25-8	Starch, edible	
88880	068412-29-3	Starch, hydrolysed	
88960	000124-26-5	Stearamide	
89040	000057-11-4	Stearic acid	
89200	007617-31-4	Stearic acid, copper salt	[ <sup>F4</sup> SML(T) = 5 mg/kg ( <sup>7</sup> ) (expressed as Copper)]
89440	—	Stearic acid, esters with ethyleneglycol	SML(T) = 30 mg/kg ( <sup>3</sup> )
90720	058446-52-9	Stearoylbenzoylmethane	
90800	005793-94-2	Stearoyl-2-lactic acid, calcium salt	
90960	000110-15-6	Succinic acid	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

91200	000126-13-6	Sucrose acetate isobutyrate	
91360	000126-14-7	Sucrose octaacetate	
91840	007704-34-9	Sulphur	
91920	007664-93-9	Sulphuric acid	
92030	010124-44-4	Sulphuric acid, copper salt	[ <sup>F4</sup> SML(T) = 5 mg/kg ( <sup>7</sup> ) (expressed as Copper)]
92080	014807-96-6	Talc	
92150	001401-55-4	Tannic acids	According to the JECFA specifications
92160	000087-69-4	Tartaric acid	
92195	—	Taurine, salts	
92205	057569-40-1	Terephthalic acid, diester with 2,2'-methylenebis(4-methyl-6-tert-butylphenol)	
92350	000112-60-7	Tetraethyleneglycol	
92640	000102-60-3	N,N,N',N'-Tetrakis(2-hydroxypropyl)ethylenediamine	
92700	078301-43-6	2,2,4,4-Tetramethyl-20-(2,3-epoxypropyl)-7-oxa-3,20-diazadispiro-[5.1.11.2]-heneicosan-21-one, polymer	SML = 5 mg/kg
92930	120218-34-0	Thiodiethanolbis(5-methoxycarbonyl-2,6-dimethyl-1,4-dihydropyridine-3-carboxylate)	SML = 6 mg/kg
93440	013463-67-7	Titanium dioxide	
93520	000059-02-9 010191-41-0	alpha-Tocopherol	
93680	009000-65-1	Tragacanth gum	
93720	000108-78-1	2,4,6-Triamino-1,3,5-triazine	SML = 30 mg/kg
94320	000112-27-6	Triethyleneglycol	

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

94960	000077-99-6	1,1,1-Trimethylolpropane	SML = 6 mg/kg
[ <sup>F2</sup> 95000	028931-67-1	Trimethylolpropane trimethacrylate-methyl methacrylate copolymer	] ]
95200	001709-70-2	1,3,5-Trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene	
95270	161717-32-4	2,4,6-Tris(tert-butyl)phenyl-2-butyl-2-ethyl-1,3-propanediol phosphite	SML = 2 mg/kg (as sum of phosphite, phosphate and the hydrolysis product = TTBP)
95725	110638-71-6	Vermiculite, reaction product with citric acid, lithium salt	SML(T) = 0,6 mg/kg ( <sup>8</sup> ) (expressed as Lithium)
95855	007732-18-5	Water	In compliance with Directive 98/83/EEC
95859	—	Waxes, refined, derived from petroleum based or synthetic hydrocarbon feedstocks	In compliance with the specifications laid down in Annex V
95883	—	White mineral oils, paraffinic, derived from petroleum based hydrocarbon feedstocks	In compliance with the specifications laid down in Annex V
95905	013983-17-0	Wollastonite	
95920	—	Wood flour and fibers, untreated	
95935	011138-66-2	Xanthan gum	
96190	020427-58-1	Zinc hydroxide	[ <sup>F5</sup> SML(T) = 25 mg/kg ( <sup>38</sup> ) (as Zinc)]
96240	001314-13-2	Zinc oxide	[ <sup>F5</sup> SML(T) = 25 mg/kg ( <sup>38</sup> ) (as Zinc)]
96320	001314-98-3	Zinc sulphide	[ <sup>F5</sup> SML(T) = 25 mg/kg ( <sup>38</sup> ) (as Zinc)]

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

### Textual Amendments

**F7** Substituted by [Commission Directive 2004/1/EC](#) of 6 January 2004 amending [Directive 2002/72/EC](#) as regards the suspension of the use of azodicarbonamide as blowing agent (Text with EEA relevance).

## Section B

### INCOMPLETE LIST OF ADDITIVES REFERRED TO IN ARTICLE 4, SECOND PARAGRAPH

Ref. No	CAS No	Name	Restrictions and/or specifications
(1)	(2)	(3)	(4)
30180	002180-18-9	Acetic acid, manganese salt	SML(T) = 0,6 mg/kg <sup>(10)</sup> (expressed as Manganese)
[ <sup>F5</sup> 31500	025134-51-4	Acrylic acid, acrylic acid, 2-ethylhexyl ester, copolymer	SML(T) = 6 mg/kg <sup>(36)</sup> (expressed as acrylic acid) and SML = 0,05 mg/kg (expressed as acrylic acid, 2-ethylhexyl ester)]
31520	061167-58-6	Acrylic acid, 2-tert-butyl-6-(3-tert-butyl-2-hydroxy-5-methylbenzyl)-4-methylphenyl ester	SML = 6 mg/kg
31920	000103-23-1	Adipic acid, bis(2-ethylhexyl) ester	SML = 18 mg/kg <sup>(1)</sup>
34230	—	Alkyl(C <sub>8</sub> -C <sub>22</sub> )sulphonic acids	SML = 6 mg/kg
[ <sup>F2</sup> 34650	151841-65-5	Aluminium hydroxybis [2,2'-methylenebis (4,6-di-tert.butylphenyl) phosphate	SML = 5 mg/kg]
35760	001309-64-4	Antimony trioxide	SML = 0,02 mg/kg (expressed as Antimony and analytical tolerance included)
36720	017194-00-2	Barium hydroxide	SML(T) = 1 mg/kg <sup>(12)</sup> (expressed as Barium)

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

36800	010022-31-8	Barium nitrate	SML(T) = 1 mg/kg <sup>(12)</sup> (expressed as Barium)
[ <sup>F2</sup> 38000	000553-54-8	Benzoic acid, lithium salt	SML(T) = 0,6 mg/kg <sup>(8)</sup> (expressed as Lithium)]
38240	000119-61-9	Benzophenone	SML = 0,6 mg/kg
[ <sup>F5</sup> 38505	351870-33-2	cis-endo-Bicyclo[2.2.1]heptane-2,3-dicarboxylic acid, disodium salt	SML = 5 mg/kg. Not to be used with polyethylene in contact with acidic foods. Purity ≥ 96 %]
38560	007128-64-5	2,5-Bis(5-tert-butyl-2-benzoxazolyl)thiophene	SML = 0,6 mg/kg
38700	063397-60-4	Bis(2-carbobutoxyethyl)tin-bis(isooctyl mercaptoacetate)	SML = 18 mg/kg
38800	032687-78-8	N,N'-Bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl)hydrazide	SML = 15 mg/kg
38820	026741-53-7	Bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite	SML = 0,6 mg/kg
[ <sup>F5</sup> 38940	110675-26-8	2,4-Bis(dodecylthiomethyl)phenol	SML(T) = 5 mg/kg <sup>(6)</sup> ]
39060	035958-30-6	1,1-Bis(2-hydroxy-3,5-di-tert-butylphenyl)ethane	SML = 5 mg/kg
39090	—	N,N-Bis(2-hydroxyethyl)alkyl(C <sub>8</sub> -C <sub>18</sub> )amine	SML(T) = 1,2 mg/kg <sup>(13)</sup>
39120	—	N,N-Bis(2-hydroxyethyl)alkyl(C <sub>8</sub> -C <sub>18</sub> )amine hydrochlorides	SML(T) = 1,2 mg/kg <sup>(13)</sup> expressed as Tertiary amine (expressed excluding HCl)
40000	000991-84-4	2,4-Bis(octylmercapto)-6-(4-hydroxy-3,5-di-tert-	SML = 30 mg/kg

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

		butylanilino)-1,3,5-triazine	
40020	110553-27-0	2,4-Bis(octylthiomethyl)-6-methylphenol	[ <sup>F4</sup> SML(T) = 5 mg/kg ( <sup>40</sup> )]
40160	061269-61-2	N,N'-Bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine-1,2-dibromoethane, copolymer	SML = 2,4 mg/kg
[ <sup>F2</sup> 40720	025013-16-5	tert-Butyl-4-hydroxyanisole (= BHA)	SML = 30 mg/kg]
40800	013003-12-8	4,4'-Butylidene-bis(6-tert-butyl-3-methylphenyl-ditridecyl phosphite)	SML = 6 mg/kg
40980	019664-95-0	Butyric acid, manganese salt	SML(T) = 0,6 mg/kg ( <sup>10</sup> ) (expressed as Manganese)
42000	063438-80-2	(2-Carbobutoxyethyl)tin-tris(isooctyl mercaptoacetate)	SML = 30 mg/kg
42400	010377-37-4	Carbonic acid, lithium salt	SML(T) = 0,6 mg/kg ( <sup>8</sup> ) (expressed as Lithium)
42480	000584-09-8	Carbonic acid, rubidium salt	SML = 12 mg/kg
43600	004080-31-3	1-(3-Chloroallyl)-3,5,7-triaza-1-azoniaadamantane chloride	SML = 0,3 mg/kg
43680	000075-45-6	Chlorodifluoromethane	SML = 6 mg/kg and in compliance with the specifications laid down in Annex V
44960	011104-61-3	Cobalt oxide	SML(T) = 0,05 mg/kg ( <sup>14</sup> ) (expressed as Cobalt)
45440	—	Cresols, butylated, styrenated	SML = 12 mg/kg

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

45650	006197-30-4	2-Cyano-3,3-diphenylacrylic acid, 2-ethylhexyl ester	SML = 0,05 mg/kg
[ <sup>F2</sup> 46640	000128-37-0	2,6-Di-tert-butyl-p-cresol (= BHT)	SML = 3,0 mg/kg]
[ <sup>F3</sup> ]			
47600	084030-61-5	Di-n-dodecyltin bis(isooctyl mercaptoacetate)	SML = 12 mg/kg
48640	000131-56-6	2,4-Dihydroxybenzophenone	SML(T) = 6 mg/kg ( <sup>15</sup> )
48800	000097-23-4	2,2'-Dihydroxy-5,5'-dichlorodiphenylmethane	SML = 12 mg/kg
48880	000131-53-3	2,2'-Dihydroxy-4-methoxybenzophenone	SML(T) = 6 mg/kg ( <sup>15</sup> )
[ <sup>F5</sup> 49595	057583-35-4	Dimethyltin bis(ethylhexyl mercaptoacetate)	SML(T) = 0,18 mg/kg ( <sup>16</sup> ) (expressed as Tin)]
49600	026636-01-1	Dimethyltin bis(isooctyl mercaptoacetate)	SML(T) = 0,18 mg/kg ( <sup>16</sup> ) (expressed as Tin)
49840	002500-88-1	Diocetyl disulphide	SML = 3 mg/kg
50160	—	Di-n-octyltin bis(n-alkyl(C <sub>10</sub> -C <sub>16</sub> ) mercaptoacetate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50240	010039-33-5	Di-n-octyltin bis(2-ethylhexyl maleate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50320	015571-58-1	Di-n-octyltin bis(2-ethylhexyl mercaptoacetate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50360	—	Di-n-octyltin bis(ethyl maleate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50400	033568-99-9	Di-n-octyltin bis(isooctyl maleate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50480	026401-97-8	Di-n-octyltin bis(isooctyl mercaptoacetate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

50560	—	Di-n-octyltin 1,4-butanediol bis(mercaptoacetate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50640	003648-18-8	Di-n-octyltin dilaurate	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50720	015571-60-5	Di-n-octyltin dimaleate	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50800	—	Di-n-octyltin dimaleate, esterified	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50880	—	Di-n-octyltin dimaleate, polymers (n = 2-4)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
50960	069226-44-4	Di-n-octyltin ethyleneglycol bis(mercaptoacetate)	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
51040	015535-79-2	Di-n-octyltin mercaptoacetate	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
51120	—	Di-n-octyltin thiobenzoate 2-ethylhexyl mercaptoacetate	[ <sup>F4</sup> SML(T) = 0,006 mg/kg ( <sup>17</sup> ) (expressed as Tin)]
51570	000127-63-9	Diphenyl sulphone	SML(T) = 3 mg/ kg ( <sup>25</sup> )
51680	000102-08-9	N,N'- diphenylthiourea	SML = 3 mg/kg
52000	027176-87-0	Dodecylbenzenesulphonic acid	SML = 30 mg/kg
52320	052047-59-3	2-(4- Dodecylphenyl)indole	SML = 0,06 mg/kg
52880	023676-09-7	4-Ethoxybenzoic acid, ethyl ester	SML = 3,6 mg/kg
53200	023949-66-8	2-Ethoxy-2'- ethyloxanilide	SML = 30 mg/kg
[ <sup>F2</sup> 54880	000050-00-0	Formaldehyde	SML(T) = 15 mg/kg ( <sup>22</sup> )
55200	001166-52-5	Gallic acid, dodecyl ester	SML(T) = 30 mg/kg ( <sup>34</sup> )



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

55280	001034-01-1	Gallic acid, octyl ester	SML(T) = 30 mg/kg <sup>(34)</sup>
55360	000121-79-9	Gallic acid, propyl ester	SML(T) = 30 mg/kg <sup>(34)</sup> ]
58960	000057-09-0	Hexadecyltrimethylammonium bromide	SML = 6 mg/kg
59120	023128-74-7	1,6-Hexamethylene-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionamide)	SML = 45 mg/kg
59200	035074-77-2	1,6-Hexamethylene-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)	SML = 6 mg/kg
60320	070321-86-7	2-[2-Hydroxy-3,5-bis(1,1-dimethylbenzyl)phenyl]benzotriazole	SML = 1,5 mg/kg
60400	003896-11-5	2-(2'-Hydroxy-3'-tert-butyl-5'-methylphenyl)-5-chlorobenzotriazole	SML(T) = 30 mg/kg <sup>(19)</sup>
60800	065447-77-0	1-(2-Hydroxyethyl)-4-hydroxy-2,2,6,6-tetramethyl piperidine-succinic acid, dimethyl ester, copolymer	SML = 30 mg/kg
61280	003293-97-8	2-Hydroxy-4-n-hexyloxybenzophenone	SML(T) = 6 mg/kg <sup>(15)</sup>
61360	000131-57-7	2-Hydroxy-4-methoxybenzophenone	SML(T) = 6 mg/kg <sup>(15)</sup>
61440	002440-22-4	2-(2'-Hydroxy-5'-methylphenyl)benzotriazole	SML(T) = 30 mg/kg <sup>(19)</sup>
61600	001843-05-6	2-Hydroxy-4-n-octyloxybenzophenone	SML(T) = 6 mg/kg <sup>(15)</sup>
63200	051877-53-3	Lactic acid, manganese salt	SML(T) = 0,6 mg/kg <sup>(10)</sup> (expressed as Manganese)
[ <sup>F5</sup> 63940	008062-15-5	Lignosulphonic acid	SML = 0,24 mg/kg and to be used only as dispersant for plastics dispersions]

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

64320	010377-51-2	Lithium iodide	SML(T) = 1 mg/kg <sup>(11)</sup> (expressed as Iodine) and SML(T) = 0,6 mg/kg <sup>(8)</sup> (expressed as Lithium)
65120	007773-01-5	Manganese chloride	SML(T) = 0,6 mg/kg <sup>(10)</sup> (expressed as Manganese)
65200	012626-88-9	Manganese hydroxide	SML(T) = 0,6 mg/kg <sup>(10)</sup> (expressed as Manganese)
65280	010043-84-2	Manganese hypophosphite	SML(T) = 0,6 mg/kg <sup>(10)</sup> (expressed as Manganese)
65360	011129-60-5	Manganese oxide	SML(T) = 0,6 mg/kg <sup>(10)</sup> (expressed as Manganese)
65440	—	Manganese pyrophosphite	SML(T) = 0,6 mg/kg <sup>(10)</sup> (expressed as Manganese)
[ <sup>F5</sup> 66350	085209-93-4	2,2'-Methylenebis(4,6-di-tert-butylphenyl) lithium phosphate	SML = 5 mg/kg and SML(T) = 0,6 <sup>(8)</sup> (expressed as Lithium)]
66360	085209-91-2	2,2'-Methylene bis(4,6-di-tert-butylphenyl) sodium phosphate	SML = 5 mg/kg
66400	000088-24-4	2,2'-Methylene bis(4-ethyl-6-tert-butylphenol)	SML(T) = 1,5 mg/kg <sup>(20)</sup>
66480	000119-47-1	2,2'-Methylene bis(4-methyl-6-tert-butylphenol)	SML(T) = 1,5 mg/kg <sup>(20)</sup>
67360	067649-65-4	Mono-n-dodecyltin tris(isooctyl mercaptoacetate)	SML = 24 mg/kg
[ <sup>F5</sup> 67515	057583-34-3	Monomethyltin tris(ethylhexyl mercaptoacetate)	SML(T) = 0,18 mg/kg <sup>(16)</sup> (expressed as Tin)]
67520	054849-38-6	Monomethyltin tris(isooctyl mercaptoacetate)	SML(T) = 0,18 mg/kg <sup>(16)</sup> (expressed as Tin)

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

67600	—	Mono-n-octyltin tris(alkyl(C <sub>10</sub> -C <sub>16</sub> ) mercaptoacetate)	SML(T) = 1,2 mg/kg ( <sup>18</sup> ) (expressed as Tin)
67680	027107-89-7	Mono-n-octyltin tris(2-ethylhexyl mercaptoacetate)	SML(T) = 1,2 mg/kg ( <sup>18</sup> ) (expressed as Tin)
67760	026401-86-5	Mono-n-octyltin tris(isooctyl mercaptoacetate)	SML(T) = 1,2 mg/kg ( <sup>18</sup> ) (expressed as Tin)
[ <sup>F2</sup> 67896	020336-96-3	Myristic acid, lithium salt	SML(T) = 0,6 mg/kg ( <sup>8</sup> ) (expressed as Lithium)]
[ <sup>F3</sup> ]			
68320	002082-79-3	Octadecyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate	SML = 6 mg/kg
68400	010094-45-8	Octadecylceramide	SML = 5 mg/kg
68860	004724-48-5	n-Octylphosphonic acid	SML = 0,05 mg/kg
[ <sup>F5</sup> 69160	014666-94-5	Oleic acid, cobalt salt	SML(T) = 0,05 mg/kg ( <sup>14</sup> ) (expressed as Cobalt)]
69840	016260-09-6	Oleilpalmitamide	SML = 5 mg/kg
[ <sup>F2</sup> 71935	007601-89-0	Perchloric acid, sodium salt monohydrate	SML = 0,05 mg/kg ( <sup>31</sup> )]
72160	000948-65-2	2-Phenylindole	SML = 15 mg/kg
72800	001241-94-7	Phosphoric acid, diphenyl 2-ethylhexyl ester	SML = 2,4 mg/kg
73040	013763-32-1	Phosphoric acid, lithium salts	SML(T) = 0,6 mg/kg ( <sup>8</sup> ) (expressed as Lithium)
73120	010124-54-6	Phosphoric acid, manganese salt	SML(T) = 0,6 mg/kg ( <sup>10</sup> ) (expressed as Manganese)
74400	—	Phosphorous acid, tris(nonyl-and/or dinonylphenyl) ester	SML = 30 mg/kg

[<sup>F6</sup>]

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

[ <sup>F5</sup> 76681	—	Polycyclopentadiene, hydrogenated	SML = 5 mg/kg ( <sup>1</sup> )
77440	—	Polyethyleneglycol diricinoleate	SML = 42 mg/kg
77520	061791-12-6	Polyethyleneglycol ester of castor oil	SML = 42 mg/kg
78320	009004-97-1	Polyethyleneglycol monoricinoleate	SML = 42 mg/kg
81200	071878-19-8	Poly[6-[(1,1,3,3-tetramethylbutyl)amino]-1,3,5-triazine-2,4-diyl]-[(2,2,6,6-tetramethyl-4-piperidyl)imino]hexamethylene[(2,2,6,6-tetramethyl-4-piperidyl)imino]	SML = 3 mg/kg
81680	007681-11-0	Potassium iodide	SML(T) = 1 mg/kg ( <sup>11</sup> ) (expressed as Iodium)
82020	019019-51-3	Propionic acid, cobalt salt	SML(T) = 0,05 mg/kg ( <sup>14</sup> ) (expressed as Cobalt)
83595	119345-01-6	Reaction product of di-tert-butylphosphonite with biphenyl, obtained by condensation of 2,4-di-tert-butylphenol with Friedel Craft reaction product of phosphorous trichloride and biphenyl	SML = 18 mg/kg and in compliance with the specifications mentioned in Annex V.
83700	000141-22-0	Ricinoleic acid	SML = 42 mg/kg
84800	000087-18-3	Salicylic acid, 4-tert-butylphenyl ester	SML = 12 mg/kg
84880	000119-36-8	Salicylic acid, methyl ester	SML = 30 mg/kg
85760	012068-40-5	Silicic acid, lithium aluminium salt(2:1:1)	SML(T) = 0,6 mg/kg ( <sup>8</sup> ) (expressed as Lithium)

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

85920	012627-14-4	Silicic acid, lithium salt	SML(T) = 0,6 mg/kg <sup>(8)</sup> (expressed as Lithium)
[ <sup>F5</sup> 85950	037296-97-2	Silicic acid, magnesium-sodium-fluoride salt	SML = 0,15 mg/kg (expressed as fluoride). Only to be used in layers of multilayers materials not coming into direct contact with food]
[ <sup>F2</sup> 86480	007631-90-5	Sodium bisulphite	SML(T) = 10 mg/kg <sup>(30)</sup> (expressed as SO <sub>2</sub> )
86800	007681-82-5	Sodium iodide	SML(T) = 1 mg/kg <sup>(11)</sup> (expressed as Iodine)
86880	—	Sodium monoalkyl dialkylphenoxybenzenedisulphonate	SML = 9 mg/kg
[ <sup>F2</sup> 86920	007632-00-0	Sodium nitrite	SML = 0,6 mg/kg
86960	007757-83-7	Sodium sulphite	SML(T) = 10 mg/kg <sup>(30)</sup> (expressed as SO <sub>2</sub> )
87120	007772-98-7	Sodium thiosulphate	SML(T) = 10 mg/kg <sup>(30)</sup> (expressed as SO <sub>2</sub> )
89170	013586-84-0	Stearic acid, cobalt salt	SML(T) = 0,05 mg/kg <sup>(14)</sup> (expressed as Cobalt)
92000	007727-43-7	Sulphuric acid, barium salt	SML(T) = 1 mg/kg <sup>(12)</sup> (expressed as Barium)
92320	—	Tetradecyl-polyethyleneglycol(EO=3-8) ether of glycolic acid	SML = 15 mg/kg
92560	038613-77-3	Tetrakis(2,4-di-tert-butyl-phenyl)-4,4'-biphenylene diphosphonite	SML = 18 mg/kg
92800	000096-69-5	4,4'-Thiobis(6-tert-butyl-3-methylphenol)	SML = 0,48 mg/kg
92880	041484-35-9	Thiodiethanol bis(3-(3,5-di-tert-butyl-4-	SML = 2,4 mg/kg

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

		hydroxy phenyl) propionate)	
93120	000123-28-4	Thiodipropionic acid, didodecyl ester	SML(T) = 5 mg/kg <sup>(21)</sup>
93280	000693-36-7	Thiodipropionic acid, dioctadecyl ester	SML(T) = 5 mg/kg <sup>(21)</sup>
[ <sup>F2</sup> 94400	036443-68-2	Triethyleneglycol bis[3-(3-tert-butyl-4-hydroxy-5-methylphenyl) propionate]	SML = 9 mg/kg]
94560	000122-20-3	Triisopropanolamine	SML = 5 mg/kg
[ <sup>F3</sup> ]			
[ <sup>F5</sup> 95265	227099-60-7	1,3,5-Tris(4-benzoylphenyl) benzene	SML = 0,05 mg/kg]
95280	040601-76-1	1,3,5-Tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione	SML = 6 mg/kg
95360	027676-62-6	1,3,5-Tris(3,5-di-tert-butyl-4-hydroxybenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione	SML = 5 mg/kg
95600	001843-03-4	1,1,3-Tris(2-methyl-4-hydroxy-5-tert-butylphenyl) butane	SML = 5 mg/kg

#### [<sup>F1</sup>ANNEX IV

#### PRODUCTS OBTAINED BY MEANS OF BACTERIAL FERMENTATION

Reference No	CAS No	Name	Restrictions and/or specifications
(1)	(2)	(3)	(4)
18888	080181-31-3	3-Hydroxybutanoic acid-3-hydroxypentanoic acid, copolymer	In compliance with specifications included in Annex V]

## ANNEX V

## SPECIFICATIONS

## Part A:

**General specifications**

The material and article manufactured by using aromatic isocyanates or colorants prepared by diazo-coupling, shall not release primary aromatic amines (expressed as aniline) in a detectable quantity (DL = 0,02 mg/kg of food or food simulant, analytical tolerance included). However, the migration value of the primary aromatic amines listed in this Directive are excluded from this restriction.

## Part B:

**Other specifications**

Ref. No	OTHER SPECIFICATIONS	
[ <sup>F2</sup> 11530	Acrylic acid, 2-hydroxypropyl ester. It may contain up to 25 % (m/m) of acrylic acid, 2-hydroxyisopropyl ester (CAS No 002918-23-2)]	
[ <sup>F1</sup> 16690	Divinylbenzene It may contain up to 45 % (m/m) of Ethylvinylbenzene	
18888	3-Hydroxybutanoic acid-3-hydroxypentanoic acid, copolymer	
	Definition	The copolymers are produced by the controlled fermentation of <i>Alcaligenes eutrophus</i> using mixtures of glucose and propanoic acid as carbon sources. The organism used has not been genetically engineered and has been derived from a single wild-type organism <i>Alcaligenes eutrophus</i> strain HI6 NCIMB 10442. Master stocks of the organism are stored as freeze-dried ampoules. A submaster/working stock is prepared from the master stock and stored in liquid nitrogen and used to prepare inocula for the fermenter. Fermenter samples will be examined daily both microscopically and for any changes in

---

**a** Quantity of substance used /quantity of formulation

---

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

	colonial morphology on a variety of agars at different temperatures. The copolymers are isolated from heat treatment bacteria by controlled digestion of the other cellular components, washing and drying. These copolymers are normally offered as formulated, melt formed granules containing additives such as nucleating agents, plasticisers, fillers, stabilisers and pigments which all conform to the general and individual specifications
Chemical name	Poly(3-D-hydroxybutanoate-co-3-D-hydroxypentanoate)
CAS number	080181-31-3
Structural formula	$  \begin{array}{cccc}  & & \text{CH}_3 & \\  & &   & \\  \text{CH}_3 & \text{O} & \text{CH}_2 & \text{O} \\    &    &   &    \\  (-\text{O}-\text{CH}-\text{CH}_2-\text{C})_m - (\text{O}-\text{CH}-\text{CH}_2-\text{C})_n  \end{array}  $ <p>where n/(m + n) greater than 0 and less or equal to 0,25</p>
Average molecular weight	Not less than 150 000 Daltons (measured by gel permeation chromatography)
Assay	Not less than 98 % poly(3-D-hydroxybutanoate-co-3-D-hydroxypentanoate) analysed after hydrolysis as a mixture of 3-D-hydroxybutanoic and 3-D-hydroxypentanoic acids
Description	White to off-white powder after isolation
Characteristics	
Identification tests:	
Solubility	Soluble in chlorinated hydrocarbons such as chloroform or

**a** Quantity of substance used /quantity of formulation



**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

	dichloromethane but practically insoluble in ethanol, aliphatic alkanes and water
Restriction	QMA for crotonic acid is 0.05 mg/6 dm <sup>2</sup>
Purity	Prior to granulation the raw material copolymer powder must contain:
— nitrogen	Not more than 2 500 mg/kg of plastic
— zinc	Not more than 100 mg/kg of plastic
— copper	Not more than 5 mg/kg of plastic
— lead	Not more than 2 mg/kg of plastic
— arsenic	Not more than 1 mg/kg of plastic
— chromium	Not more than 1 mg/kg of plastic]
23547	Polydimethylsiloxane (Mw > 6 800)
	Minimum viscosity $100 \times 10^{-6} \text{ m}^2/\text{s}$ (= 100 centistokes) at 25 °C
[ <sup>F5</sup> 24903	Syrups, hydrolysed starch, hydrogenated
	In compliance with the purity criteria for maltitol syrup E 965(ii) (Commission Directive 95/31/EC (OJ L 178, 28.7.1995, p. 1) as last amended by 2004/46/EC (OJ L 114, 21.04.2004, p. 15))]
25385	Triallylamine
	40 mg/kg hydrogel at a ratio of 1 kg food to a maximum of 1,5 grams of hydrogel. For use only in hydrogels intended for non-direct food contact use.
38320	4-(2-Benzoxazolyl)-4'-(5-methyl-2-benzoxazolyl) stilbene
	Not more than 0,05 %w/w (quantity of substance used/ quantity of the formulation)
[ <sup>F5</sup> 43480	Charcoal, activated
	To be used only in PET at maximum 10 mg/kg of polymer. Same purity requirements as for Vegetable Carbon (E 153) set out by Commission Directive 95/45/EC ((OJ L 226, 22.9.1995, p. 1). Directive as last amended by Directive

a Quantity of substance used /quantity of formulation

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

	2004/47/EC (OJ L 113, 20.4.2004, p. 24)) with exception of ash content which can be up to 10 % (w/w)]
43680	Chlorodifluoromethane Content of chlorofluoromethane less than 1 mg/kg of the substance
47210	Dibutylthiostannoic acid polymer Molecular unit = (C <sub>8</sub> H <sub>18</sub> S <sub>3</sub> Sn <sub>2</sub> ) <sub>n</sub> (n = 1,5-2)
[ <sup>F5</sup> 64990	Maleic anhydride-styrene, copolymer, sodium salt MW fraction < 1 000 is less than 0,05 % (w/w)
67155	Mixture of 4-(2-Benzoxazolyl)-4'-(5-methyl-2-benzoxazolyl)stilbene, 4,4'-bis(2-benzoxazolyl) stilbene and 4,4'-bis(5-methyl-2-benzoxazolyl)stilbene Mixture obtained from the manufacturing process in the typical ratio of (58-62 %):(23-27 %): (13-17 %)]
76721	Polydimethylsiloxane (Mw > 6 800) Minimum viscosity 100 × 10 <sup>-6</sup> m <sup>2</sup> /s (= 100 centistokes) at 25 °C
[ <sup>F5</sup> 76845	Polyester of 1,4-butanediol with caprolactone MW fraction < 1 000 is less than 0,05 % (w/w)
76815	Polyester of adipic acid with glycerol or pentaerythritol, esters with even numbered, unbranched C12-C22 fatty acids MW fraction < 1 000 is less than 5 % (w/w)]
[ <sup>F2</sup> 77895	Polyethyleneglycol (EO = 2-6) monoalkyl (C <sub>16</sub> -C <sub>18</sub> ) ether The composition of this mixture is as follows: — polyethyleneglycol (EO = 2-6)monoalkyl (C <sub>16</sub> -C <sub>18</sub> ) ether (approximately 28 %) — fatty alcohols (C <sub>16</sub> -C <sub>18</sub> ) (approximately 48 %) — ethyleneglycol monoalkyl (C <sub>16</sub> -C <sub>18</sub> ) ether (approximately 24 %)]
[ <sup>F5</sup> 79600	Polyethyleneglycol tridecyl ether phosphate Polyethyleneglycol (EO ≤ 11) tridecyl ether phosphate (mono-and dialkyl ester) with a maximum 10 % content of polyethyleneglycol (EO ≤ 11) tridecylether]
83595	Reaction product of di-tert-butylphosponite with biphenyl, obtained by condensation of 2,4-di-tert-butylphenol with Friedel Craft reaction product of phosphorous trichloride and biphenyl Composition:
a	Quantity of substance used /quantity of formulation

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

	<ul style="list-style-type: none"> <li>— 4,4'-Biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS.No 38613-77-3) (36-46 % w/w <sup>a</sup>),</li> <li>— 4,3'-Biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS.No 118421-00-4) (17-23 % w/w <sup>a</sup>),</li> <li>— 3,3'-Biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS.No 118421-01-5) (1-5 % w/w <sup>a</sup>),</li> <li>— 4-Biphenylene-0,0-bis(2,4-di-tert-butylphenyl)phosphonite (CAS.No 91362-37-7) (11-19 % w/w <sup>a</sup>),</li> <li>— Tris(2,4-di-tert-butylphenyl)phosphite (CAS.No 31570-04-4) (9-18 % w/w <sup>a</sup>),</li> <li>— 4,4'-Biphenylene-0,0-bis(2,4-di-tert-butylphenyl)phosphonate-0,0-bis(2,4-di-tert-butylphenyl)phosphonite (CAS.No 112949-97-0) (&lt; 5 % w/w <sup>a</sup>).</li> </ul>
	<p>Other specifications:</p> <ul style="list-style-type: none"> <li>— Phosphor content of min. 5,4 % to max. 5,9 %</li> <li>— Acid value of max. 10 mg KOH per gram</li> <li>— Melt range of 85-110 °C</li> </ul>
88640	Soybean oil, epoxidized
	Oxirane < 8 %, iodine number < 6
95859	Waxes, refined, derived from petroleum based or synthetic hydrocarbon feedstocks
	<p>The product should have the following specifications:</p> <ul style="list-style-type: none"> <li>— Content of mineral hydrocarbons with Carbon number less than 25, not more than 5 % (w/w)</li> <li>— Viscosity not less than <math>11 \times 10^{-6} \text{ m}^2/\text{s}</math> (= 11 centistokes) at 100 °C</li> <li>— Average molecular weight not less than 500.</li> </ul>
95883	White mineral oils, paraffinic derived from petroleum based hydrocarbon feedstocks
	<p>The product should have the following specifications:</p> <ul style="list-style-type: none"> <li>— Content of mineral hydrocarbons with Carbon number less than 25, not more than 5 % (w/w)</li> <li>— Viscosity not less than <math>8,5 \times 10^{-6} \text{ m}^2/\text{s}</math> (= 8,5 centistokes) at 100 °C</li> <li>— Average molecular weight not less than 480</li> </ul>
<b>a</b>	Quantity of substance used /quantity of formulation

[<sup>F1</sup>ANNEX VI

NOTES RELATED TO THE COLUMN 'RESTRICTIONS AND/OR SPECIFICATIONS'

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

- (<sup>1</sup>) Warning: there is a risk that the SML could be exceeded in fatty food simulants.
- (<sup>2</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration of the following substances mentioned as reference Nos: 10060 and 23920.
- (<sup>3</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration of the following substances mentioned as reference Nos: 15760, 16990, 47680, 53650 and 89440.
- (<sup>4</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration of the following substances mentioned as reference Nos: 19540, 19960 and 64800.
- (<sup>5</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration of the following substances mentioned as reference Nos: 14200, 14230 and 41840.
- (<sup>6</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration of the following substances mentioned as reference Nos: 66560 and 66580.
- (<sup>7</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 30080, 42320, 45195, 45200, 53610, 81760, 89200 and 92030.
- [<sup>F4</sup>(<sup>8</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 38000, 42400, 64320, 66350, 67896, 73040, 85760, 85840, 85920 and 95725.]
- (<sup>9</sup>) Warning: there is a risk that the migration of the substance deteriorates the organoleptic characteristics of the food in contact and then, that the finished product does not comply with the second indent of Article 2 of Directive 89/109/EEC.
- (<sup>10</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 30180, 40980, 63200, 65120, 65200, 65280, 65360, 65440 and 73120.
- (<sup>11</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels (expressed as Iodine) of the following substances mentioned as reference Nos: 45200, 64320, 81680 and 86800.
- (<sup>12</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 36720, 36800, 36840 and 92000.
- (<sup>13</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 39090 and 39120.
- [<sup>F4</sup>(<sup>14</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 44960, 68078, 69160, 82020 and 89170.]
- (<sup>15</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 15970, 48640, 48720, 48880, 61280, 61360 and 61600.

- [<sup>F4</sup>(<sup>16</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 49595, 49600, 67520, 67515 and 83599.]
- (<sup>17</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 50160, 50240, 50320, 50360, 50400, 50480, 50560, 50640, 50720, 50800, 50880, 50960, 51040 and 51120.
- (<sup>18</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 67600, 67680 and 67760.
- (<sup>19</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 60400, 60480 and 61440.
- (<sup>20</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 66400 and 66480.
- (<sup>21</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 93120 and 93280.
- (<sup>22</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 17260, 18670, 54880 and 59280.
- (<sup>23</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 13620, 36840, 40320 and 87040.
- (<sup>24</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 13720 and 40580.
- (<sup>25</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 16650 and 51570.
- (<sup>26</sup>) QM(T) in this specific case means that the restriction shall not be exceeded by the sum of the residual quantities of the following substances mentioned as reference Nos: 14950, 15700, 16240, 16570, 16600, 16630, 18640, 19110, 22332, 22420, 22570, 25210, 25240 and 25270.
- (<sup>27</sup>) QMA(T) in this specific case means that the restriction shall not be exceeded by the sum of the residual quantities of the following substances mentioned as reference Nos: 10599/90A, 10599/91, 10599/92A and 10599/93.
- (<sup>28</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 13480 and 39680.
- (<sup>29</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 22775 and 69920.

---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

- (<sup>30</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 86480, 86960 and 87120
- (<sup>31</sup>) Compliance testing when there is a fat contact should be performed using saturated fatty food simulants as simulant D.
- (<sup>32</sup>) Compliance testing when there is a fat contact should be performed using isoctane as substitute of simulant D (unstable).
- (<sup>33</sup>) QMA(T) in this specific case means that the restriction shall not be exceeded by the sum of the residual quantities of the following substances mentioned as reference Nos: 14800 and 45600.
- (<sup>34</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as reference Nos: 55200, 55280 and 55360.
- [<sup>F5</sup>(<sup>35</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 25540 and 25550.
- (<sup>36</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 10690, 10750, 10780, 10810, 10840, 11470, 11590, 11680, 11710, 11830, 11890, 11980 and 31500.
- (<sup>37</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 20020, 20080, 20110, 20140, 20170, 20890, 21010, 21100, 21130, 21190, 21280, 21340 and 21460.
- (<sup>38</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 81515, 96190, 96240 and 96320 as well as of salts (including double salts and acid salts) of zinc of authorised acids, phenols or alcohols. The same restriction for Zn applies to the names containing ‘... acid(s), salts’ which appear in the lists, if the corresponding free acid(s) is (are) not mentioned.
- (<sup>39</sup>) Migration limit might be exceeded at very high temperature.
- (<sup>40</sup>) SML(T) in this specific case means that the restriction shall not be exceeded by the sum of the migration levels of the following substances mentioned as Reference Nos 38940 and 40020.]]

## ANNEX VII

## Part A

**REPEALED DIRECTIVE AND ITS AMENDMENTS***(Referred to by Article 10(1))*

Commission Directive 90/128/EEC (OJ L 349, 13.12.1990, p. 26)

Commission Directive 92/39/EEC (OJ L 168, 23.6.1992, p. 21)

Commission Directive 93/9/EEC (OJ L 90, 14.4.1993, p. 26)

Commission Directive 95/3/EC (OJ L 41, 23.2.1995, p. 44)

Commission Directive 96/11/EC (OJ L 61, 12.3.1996, p. 26)

Commission Directive 1999/91/EC (OJ L 310, 4.12.1999, p. 41)

Commission Directive 2001/62/EC (OJ L 221, 17.8.2001, p. 18)

Commission Directive 2002/17/EC (OJ L 58, 28.2.2002, p. 19)

## Part B

**DEADLINES FOR TRANSPOSITION INTO NATIONAL LAW***(Referred to by Article 10(1))*

Directive	Deadlines		
	For transposition	To permit trade in those products which comply with this Directive	To prohibit trade in those products which do not comply with this Directive
90/128/EEC (OJ L 349, 13.12.1990, p. 26)	31 December 1990	1 January 1991	1 January 1993
92/39/EEC (OJ L 168, 23.6.1992, p. 21)	31 December 1992	31 March 1994	1 April 1995
93/9/EEC (OJ L 90, 14.4.1993, p. 26)	1 April 1994	1 April 1994	1 April 1996
95/3/EC (OJ L 41, 23.2.1995, p. 44)	1 April 1996	1 April 1996	1 April 1998
96/11/EC (OJ L 61, 12.3.1996, p. 26)	1 January 1997	1 January 1997	1 January 1999
1999/91/EC (OJ L 310, 4.12.1999, p. 41)	31 December 2000	1 January 2002	1 January 2003

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

2001/62/EC (OJ L 221, 17.8.2001, p. 18)	30 November 2002	1 December 2002	1 December 2002
2002/17/EC (OJ L 58, 28.2.2002, p. 19)	28 February 2003	1 March 2003	1 March 2004 1 March 2003 for materials and articles which contain Divinylbenzene

## ANNEX VIII

## CORRELATION TABLE

<b>Directive 90/128/EEC</b>	<b>This Directive</b>
Article 1	Article 1
Article 2	Article 2
Article 3	Article 3
Article 3a	Article 4
Article 3b	Article 5
Article 3c	Article 6
Article 4	Article 7
Article 5	Article 8
Article 6	Article 9
	Article 10
	Article 11
	Article 12
ANNEX I	ANNEX I
ANNEX II	ANNEX II
ANNEX III	ANNEX III
ANNEX IV	ANNEX IV
ANNEX V	ANNEX V
ANNEX VI	ANNEX VI
	ANNEX VII
	ANNEX VIII]



---

*Status: EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.*

---

- (1) [<sup>X1</sup>OJ L 40, 11.2.1989, p. 38.
- (2) OJ L 75, 21.3.1990, corrected by OJ L 349, 13.12.1990, p. 26.
- (3) OJ L 58, 28.2.2002, p. 19.
- (4) OJ L 297, 23.10.1982, p. 26. Directive as last amended by Directive 97/48/EC (OJ L 222, 12.8.1997, p. 10).
- (5) OJ L 372, 31.12.1985, p. 14.
- (6) OJ L 44, 15.2.1978, p. 15.
- (7) OJ L 213, 16.8.1980, p. 42.
- (8) OJ L 167, 24.6.1981, p. 6.
- (9) OJ L 151, 19.6.1980, p. 21.
- (10) OJ L 93, 17.4.1993, p. 27. Directive amended by Directive 93/111/EC (OJ L 310, 14.12.1993, p. 41).
- (11) [<sup>F2</sup>OJ L 40, 11.2.1989, p. 27.
- (12) OJ L 184, 15.7.1988, p. 61.]
- (13) [<sup>F1</sup>OJ L 178, 28.7.1995, p. 1.
- (14) OJ L 226, 22.9.1995, p. 1.
- (15) OJ L 292, 28.10.2002, p. 1.]]

---

#### **Editorial Information**

- X1** Substituted by [Corrigendum to Commission Directive 2002/72/EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs \(Official Journal of the European Communities L 220 of 15 August 2002\)](#).

---

#### **Textual Amendments**

- F1** Substituted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).
- F2** Inserted by [Commission Directive 2004/19/EC of 1 March 2004 amending Directive 2002/72/EC relating to plastic materials and articles intended to come into contact with foodstuffs \(Text with EEA relevance\)](#).