

SCHEDULE 2

PART I

BASIC RULES FOR DETERMINING THE MIGRATION OF LEAD AND CADMIUM

Test conditions

- 2.—(1) Carry out the test at a temperature of $22 \pm 2^\circ$ for a duration of 24 ± 0.5 hours.
- (2) When the migration of lead is to be determined, cover the sample by an appropriate means of protection and expose it to the usual lighting conditions in a laboratory.
- (3) When the migration of cadmium or of lead and cadmium is to be determined, cover the sample so as to ensure that the surface to be tested is kept in total darkness.