
Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 142/2011, Division Section 6. (See end of Document for details)

ANNEX X

FEED MATERIALS

CHAPTER II

SPECIFIC REQUIREMENTS FOR PROCESSED ANIMAL PROTEIN AND OTHER DERIVED PRODUCTS

Section 6

Specific requirements for dicalcium phosphate

A. Raw materials

Only animal by-products which are Category 3 material or products which are derived from such animal by-products, other than materials referred to in Article 10(m), (n), (o) and (p) of Regulation (EC) No 1069/2009 may be used for the production of dicalcium phosphate.

B. Processing standards

1. Dicalcium phosphate must be produced by a process that comprises the three following stages:
 - (a) firstly, ensures that all bone that is Category 3 material is finely crushed and degreased with hot water and treated with dilute hydrochloric acid (at a minimum concentration of 4 % and a pH of less than 1,5) over a period of at least two days;
 - (b) secondly, following the part of the process referred to in point (a), applies a treatment of the obtained phosphoric liquor with lime, resulting in a precipitate of dicalcium phosphate at pH 4 to 7;
 - (c) finally, air-dries the precipitate of dicalcium phosphate with inlet temperature of 65 °C to 325 °C and end temperature between 30 °C and 65 °C.
2. Where dicalcium phosphate is derived from defatted bones, it shall be derived from bones referred to in Article 10(a) of Regulation (EC) No 1069/2009.

Changes to legislation:

There are currently no known outstanding effects for the Commission Regulation (EU) No 142/2011, Division Section 6.