
STATUTORY RULES OF NORTHERN IRELAND

2008 No. 271

FOOD

**The Plastic Materials and Articles in Contact with Food
(Amendment) Regulations (Northern Ireland) 2008**

<i>Made</i>	- - - -	<i>26th June 2008</i>
<i>Coming into operation</i>		
<i>for the purpose of</i>		
<i>regulation 6</i>		<i>30th June 2008</i>
<i>for all other purposes</i>		<i>1st July 2008</i>

The Department of Health, Social Services and Public Safety⁽¹⁾ makes the following Regulations in exercise of the powers conferred on it by Articles 15(2), 16(1) and (2), 25(1)(a), (2)(a) and (3), 32 and 47(2) of [the Food Safety \(Northern Ireland\) Order 1991](#)⁽²⁾.

In accordance with Article 47(3A) of that Order, it has had regard to relevant advice given by the Food Standards Agency.

As required by Article 9 of [Regulation \(EC\) No. 178/2002 of the European Parliament and of the Council](#) laying down the general principles and requirements of food law, establishing the European Food Safety Authority and laying down procedures in matters of food safety⁽³⁾, there has been open and transparent public consultation during the preparation and evaluation of these Regulations.

Citation and commencement

1. These Regulations may be cited as the Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008 and come into operation —

- (a) for the purpose of regulation 6 on 30th June 2008, and
- (b) for all other purposes on 1st July 2008.

(1) Formerly the Department of Health and Social Services; see [S.I. 1999/283 \(N.I.1\)](#) Article 3(6)
(2) [S.I. 1991/762 \(N.I.7\)](#) as amended by [S.I. 1996/1663 \(N.I.12\)](#), paragraphs 26 to 42 of [Schedule 5](#) and [Schedule 6 to the Food Standards Act 1999](#) c.28 and [S.R. 2004 Nos. 482 and 505](#)
(3) OJ No. L31, 1.2.2002, p.1: that Regulation was last amended by Commission Regulation (EC) No. 202/2008 (OJ No. L60, 5.3.2008, p.17)

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

Commencement Information

I1 Reg. 1 in operation at 1.7.2008, see [reg. 1\(b\)](#)

Amendments to the Plastic Materials and Articles in Contact with Food Regulations (Northern Ireland) 2008

- ^{F1}**2.**
- ^{F1}**3.**
- ^{F1}**4.**
- ^{F1}**5.**
- ^{F1}**6.**
- ^{F1}**7.**

Textual Amendments

F1 [Regs. 2-7](#) revoked (13.3.2009) by [The Plastic Materials and Articles in Contact with Food Regulations \(Northern Ireland\) 2009 \(revoked\) 2009 \(S.R. 2009/56\)](#), [regs. 1, 26\(b\)](#)

Amendment of the Plastic Materials and Articles in Contact with Food (Lid Gaskets) Regulations (Northern Ireland) 2007

8. In regulation 2(1) (interpretation) of the Plastic Materials and Articles in Contact with Food (Lid Gaskets) Regulations (Northern Ireland) 2007(4), for the definition of “the Commission Regulation” substitute —

““the Commission Regulation” means [Commission Regulation \(EC\) No 372/2007](#) laying down transitional migration limits for plasticisers in gaskets in lids intended to come into contact with foods as amended by [Commission Regulation \(EC\) No 597/2008](#); amending [Commission Regulation \(EC\) No. 372/2007](#) laying down transitional migration limits for plasticisers in gaskets in lids intended to come into contact with foods(5)

Commencement Information

I2 Reg. 8 in operation at 1.7.2008, see [reg. 1\(b\)](#)

Amendment of the Food Safety (Sampling and Qualifications) Regulations (Northern Ireland) 1991

9. In the Food Safety (Sampling and Qualifications) Regulations (Northern Ireland) 1991(6), in Schedule 1 (provisions to which those Regulations do not apply) for the title and reference of the Plastic Materials and Articles in Contact with Food (No. 2) Regulations (Northern Ireland) 2006 substitute the title and reference of the Plastic Materials and Articles in Contact with Food Regulations (Northern Ireland) 2008.

(4) [S.R. 2007 No. 419](#)
(5) [OJ No. L164, 25.6.2008, p. 12](#)
(6) [S.R. 1991 No. 198](#); the relevant amending Regulation is [S.R. 2006 No. 420](#)

Changes to legislation: *There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes*

.....

Commencement Information

I3 Reg. 9 in operation at 1.7.2008, see [reg. 1\(b\)](#)

Sealed with the Official Seal of the Department of Health, Social Services and Public Safety on 26th June 2008.



Andrew McCormick
A senior officer of the Department of Health,
Social Services and Public Safety

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

SCHEDULE

Regulation 7

Commencement Information

I4 Sch. in operation at 1.7.2008, see [reg. 1\(b\)](#)

“SCHEDULE 1

Regulations 4 and 5

Supplementary provisions relating to Annexes II and III

1. In Sections A and B of Annexes II and III (for the purposes of this Schedule referred to together as “the Annexes”) —

- (a) the PM/REF number of any substance is its EEC packaging material reference number;
- (b) the CAS number of any substance is its CAS (Chemical Abstracts Service) Registry Number;
- (c) the name of any substance is its chemical name, and to the extent that there is any inconsistency between the CAS number and the name, the name shall take precedence over the CAS number; and
- (d) references to specific migration are to be taken to mean specific migration as measured in accordance with Schedules 2 and 3.

2. If a substance appearing in the Annexes as an individual compound also falls within a generic term which appears therein, any restriction applying to that substance shall be that indicated for the individual compound and the entry applying to the generic term shall be treated as varied to such extent as is necessary.

3.—(1) The items identified in Section A or B of Annex II shall be taken to include—

- (a) substances undergoing polymerisation (including polycondensation, polyaddition or any other similar process) to manufacture macromolecules;
- (b) natural or synthetic macromolecular substances used in the manufacture of modified macromolecules, if the monomers required to synthesise them are not so identified; and
- (c) substances used to modify existing natural or synthetic macromolecular substances.

(2) Salts (including double salts and acid salts) of aluminium, ammonium, calcium, iron, magnesium, potassium and sodium of authorised acids, phenols or alcohols are not included in the lists in the Annexes even if they are authorised and intentionally used; however names containing “...acid(s), salts” do appear in the lists if the corresponding free acid(s) is or are not mentioned.

(3) Salts (including double salts and acid salts) of zinc of authorised acids, phenols or alcohols are not included in the lists in the Annexes even if they are authorised and intentionally used. For these salts a Group SML = 25/mg/kg (expressed as Zn) applies. The same restriction for Zn applies to —

- (a) substances whose name contains “...acid(s), salts” which appear in the lists, if the corresponding free acid(s) is or are not mentioned; and
- (b) substances referred to in note 38 of Annex VI.

4. In the case of substances listed in Section B of Annex III, the specific migration limits specified in column 4 shall have effect where the verification of compliance is carried out in Simulant D or in test media of substitute tests as prescribed in Directive [82/711/EEC](#) and [85/572/EEC](#).

5. Where an entry in column 4 of the Annexes (restrictions and specifications) includes a bracketed number, that entry shall be subject to a note relating to that number as set out in Annex VI.

SCHEDULE 2

Regulations 9 and 13

Provisions Applicable when Testing Compliance with the Migration Limits

General Provisions

1. When the results of the migration tests specified in this Schedule and, where appropriate Schedule 3, are analytically determined, the specific gravity of any simulants used shall be assumed to be 1, so that milligrams of any substance released per litre of simulant will correspond numerically to milligrams of that substance released per kilogram of that simulant.

2. Where any migration test specified in this Schedule and, where appropriate, Schedule 3 is carried out on any sample taken from any plastic material or article and the quantities of food or simulant placed in contact with the sample differ from those employed in the actual conditions under which the plastic material or article is used or is to be used, the results obtained should be corrected by applying the formula $M = ((m \cdot a_2 / a_1 \cdot q) \cdot 1000)$ where —

- (a) M is the migration in mg/kg;
- (b) m is the mass in the mg of substance released by the sample as determined by the migration test;
- (c) a_1 is the surface area in square decimetres of the sample in contact with the food or simulant during the migration test;
- (d) a_2 is the surface area in square decimetres of the plastic material or article in actual conditions of use; and
- (e) q is the quantity in grams of food in contact with the plastic material or article in actual conditions of use.

3.—(1) Subject to sub-paragraph (2), any testing of migration from any plastic material or article shall be carried out on that plastic material or article.

(2) In any case where determination in accordance with sub-paragraph (1) above is impracticable, such testing shall be carried out, using either specimens taken from that plastic material or article, or where appropriate, specimens representative of that plastic material or article.

(3) Any sample used for such testing shall be placed in contact with the simulant or food, as the case may be, in a manner representing the contact conditions in actual use, and for this purpose the testing shall be carried out in such a way that only those parts of the sample intended to come into contact with food in actual use will be in contact with the simulant or food.

(4) Any migration testing of caps, gaskets, stoppers or similar devices for sealing shall be carried out on these articles by applying them to the containers for which they are intended in a manner which corresponds to the conditions of closing in normal or foreseeable use.

4.—(1) Any sample of plastic material or article shall be placed in contact with the appropriate simulant or the food for a period and at a temperature which are chosen by reference to the contact conditions in actual use in accordance with the provisions of this Schedule and, where appropriate, Schedule 3.

(2) At the end of the period referred to in sub-paragraph (1), analytical determination of the total quantity of substances (overall migration), each specific quantity of a substance (specific migration) or, as the case may be, both that total and that specific quantity released by the sample shall be carried out on the simulant or food, as the case may be.

(3) Verification that migration into food complies with a migration limit specified in regulation 9 or in Annex II, III or IV (for the purposes of this Schedule and Schedule 3 referred to together

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

as “the Annexes”) shall be carried out under the most extreme conditions of time and temperature foreseeable in actual use in accordance with the provisions of this Schedule.

(4) Verification that migration into food simulants complies with a migration limit specified in regulation 9 or the Annexes shall be carried out in accordance with the provisions of this Schedule and using conventional migration tests, the basic rules for which are set out in Schedule 3.

5. Where a plastic material or article is intended to come into repeated contact with food, any migration test shall (subject to paragraph 7) be carried out three times on a single sample in accordance with the conditions laid down in this Schedule and, where appropriate, Schedule 3 using separate samples of the simulant or, as the case may be, food on each occasion, and the level of the migration found in the third test shall be treated as the level relevant to that test.

Special provisions relating to the fat reduction factor

6.—(1) Subject to paragraph 7, the results of tests for specific migration in foods containing more than 20% fat shall be corrected by the fat reduction factor (“FRF”), being a factor between 1 and 5 (expressed as M_{FRF}) by which measured migration of lipophilic substances listed in Annex IVa into a fatty food or simulant D and its substitutes are divided before comparison with specific migration limits.

(2) The following equations shall be applied before comparison with the specific migration limit —

- (a) $M_{FRF} = M/FRF$, and
- (b) $FRF = (\text{g fat in food/kg of food})/200 = (\% \text{ fat} \times 5)/100$.

7.—(1) Correction by the FRF may not be used —

- (a) where the plastic material or article is in contact or is intended to be brought into contact with foods intended for infants and young children;
- (b) for substances listed in the Annexes having a restriction in column (4) of SML = ND;
- (c) for substances not listed in the Annexes and used behind a plastic functional barrier with a migration limit of 0.01 mg/kg;
- (d) except in the circumstances specified in sub-paragraph (2), for plastic materials or articles —
 - (i) for which it is impracticable to estimate the relationship between the surface area and the quantity of food in contact with it, due to shape, use or other factors, and
 - (ii) where the migration is calculated using the conventional surface area/volume conversion factor of 6 dm²/kg.

(2) For containers and other fillable articles with a capacity of less than 500 millilitres or more than 10 litres and for sheets and films in contact with foods containing more than 20% fat —

- (a) the migration may be calculated as concentration (expressed as mg/kg) in the food or food simulant and corrected by the FRF; or
- (b) the migration may be re-calculated as mg/dm² without applying the FRF,

and provided the value resulting from the calculation under either sub-paragraph (a) or (b) is below the SML the plastic material or article shall be considered to be in compliance.

8. If use of the FRF under paragraph 6 or 7(2) produces a result that indicates the overall migration limit has been exceeded, the plastic material or article in question shall not be considered to be in compliance.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) [View outstanding changes](#)

Special provisions relating to the correction of specific migration in simulant D

9. The specific migration of those lipophilic substances listed in Annex IVa into simulant D and its substitutes shall be corrected by —

- (a) the simulant D reduction factor (“DRF”), being the reduction factor referred to in paragraph 2(2) of Part 3 and paragraphs 2 and 3 of Part 4 of Schedule 3, provided that —
 - (i) in cases where the specific migration into simulant D is higher than 80% of the content of the substance in the finished plastic material or article, it can be demonstrated by scientific or experimental evidence, such as testing with the most critical foods, that the DRF is appropriate, and
 - (ii) the substance is not one mentioned in paragraph 7(1)(b) or (c);
- (b) the FRF, provided that the fat content of the food to be packed is known and the requirements of paragraphs 6, 7 and 8 are fulfilled; or
- (c) the total reduction factor (“TRF”), being the factor —
 - (i) by which a measured specific migration into simulant D or a substitute shall be divided before comparison with the specific migration limit, and
 - (ii) which is obtained by multiplying the DRF by the FRF with a maximum value of 5, when both factors are applicable.

Special provisions relating to overall migration

10.—(1) Subject to sub-paragraph (2), any method of analytical determination may be used to prove excess of an overall migration limit in relation to a plastic material or article.

(2) In any proceedings for an offence under these Regulations where it is alleged that a plastic material or article does not comply with regulation 9 it shall be a defence for the person charged to prove that—

- (a) if an aqueous simulant specified in Schedule 3 had been used, and the analytical determination of the total quantity of substances released by a sample of the plastic material or article tested had been carried out by evaporation of the simulant and weighing of the residue; or
- (b) if rectified olive oil or any of its substitutes had been used as a simulant and—
 - (i) a sample of the plastic material or article had been weighed before and after contact with the simulant;
 - (ii) the simulant absorbed by the sample had been extracted and determined quantitatively;
 - (iii) the quantity of simulant so found had been subtracted from the weight of the sample measured after contact with the simulant; and
 - (iv) the difference between the initial and corrected final weights had been determined to represent the overall migration of the sample examined,

there would have been no such excess so determined.

11.—(1) Where a plastic material or article is intended to come into repeated contact with food and it is technically impossible to carry out the test described in paragraph 5, the test shall be modified in accordance with sub-paragraph (2) or in such other way so as to enable the level of migration occurring during the third such test to be determined, and such a determination may be used as evidence of the overall migration in relation to a plastic material or article.

(2) Three identical samples of the plastic material or article are to be procured, following which—

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

- (a) the first sample is to be subjected to the appropriate test according with paragraph 4 and the overall migration determined (M_1);
 - (b) the second and third samples are to be subjected to the same conditions of temperature but the period of contact is to be respectively two and three times that specified and the overall migration determined in each case (M_2 and M_3).
- (3) Where a modified test has been carried out in accordance with sub-paragraph (2), provided that either M_1 or $M_3 - M_2$ did not exceed the overall migration limit, the plastic material or article subjected to the test shall be deemed to be in compliance with that limit.

12.—(1) Any plastic material or article which exceeds its overall migration limit by an amount not exceeding the analytical tolerance specified in sub-paragraph (2) shall be deemed for the purposes of these Regulations not to exceed its overall migration limit.

- (2) The following analytical tolerances shall be applied for limits of overall migration—
- (a) 20 mg/kg or, as the case may be, 3 milligrams per square decimetre in migration tests using as a simulant rectified olive oil or substitutes;
 - (b) 12mg/kg or, as the case may be, 2 milligrams per square decimetre in migration tests using other simulants referred to in Schedule 3.

Special provisions relating to caps, lids, gaskets, stoppers and similar sealing articles

13.—(1) If the intended use is known, caps, lids, gaskets, stoppers and similar sealing articles shall be tested by applying them to the containers for which they are intended under conditions of closure corresponding to the normal or foreseeable use and on the assumption that such articles are in contact with a quantity of food filling the container.

(2) The results of any tests carried out under sub-paragraph (1) shall be expressed in mg/kg or mg/dm^2 as appropriate in accordance with the requirements of regulation 9(2), taking into account the total contact surface of sealing article and container that is potentially in contact with the food.

(3) If the intended use of an article of the type mentioned in sub-paragraph (1) is not known, it shall be —

- (a) tested separately from the container for which it is intended, with the result being expressed in mg/article; and
- (b) the value added, if appropriate, to the quantity migrated from that container.

SCHEDULE 3

Regulations 9 and 13

Overall and Specific Migration Testing Using Food Simulants

PART 1

Basic Rules

1. Subject to paragraphs 2, 3 and 4 of this Part, migration tests for the determination of specific and overall migration shall be carried out using the food simulants specified in Parts 2, 3 and, where appropriate 4, and under conventional migration test conditions as specified in Part 5.

2. Subject to paragraphs 3 and 4 of this Part, substitute tests which use test media under the conventional substitute test conditions as specified in Part 6 shall be carried out if the migration test

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

using the fatty food simulants specified in Part 3 is not feasible for technical reasons connected with the method of analysis.

3. Subject to paragraph 4 of this Part, alternative tests as specified in Part 7 may be used instead of the migration test with fatty food simulants specified in Part 3 but the results of such alternative tests may not be used to determine compliance with a migration limit unless the conditions specified in Part 7 are fulfilled.

4. In migration testing it is permissible to—

- (a) reduce the number of tests to be carried out to that or those which, in the specific case under examination, is or are generally recognised to be the most severe on the basis of scientific evidence;
- (b) omit the migration, the substitute or the alternative tests where —
 - (i) there is conclusive proof that the migration limits cannot be exceeded in any foreseeable conditions of use of the material or article, or
 - (ii) the conditions for non-compulsory testing set out in Article 8(2) or 8(3) of the Directive are met.

PART 2

Food Simulants to be used in Migration Testing

1. Subject to Parts 3, 4, 5 and 7, the simulants to be used in migration testing are specified in the Table to this paragraph (referred to in this Part as “the Table”).

<i>I</i>	<i>2</i>
<i>Abbreviation</i>	<i>Food Simulant</i>
Simulant A:	Distilled water or water of equivalent quality
Simulant B:	3% Acetic acid (w/v) in aqueous solution
Simulant C:	10% Ethanol (v/v) in aqueous solution except that the concentration of ethanol solution shall be adjusted to the actual alcoholic strength of the food if it exceeds 10% (v/v)
Simulant D:	Rectified olive oil having the characteristics specified in paragraph 3 or, subject to paragraph 5, any of the fatty food simulants specified in paragraph 4

2. For the purposes of this Schedule a reference to an abbreviation in column 1 of the Table means a reference to the simulant in column 1 of that Table opposite that abbreviation.

3. The characteristics of rectified olive oil referred to in the Table are —

- (a) Iodine value (Wijs) = 80 to 88;
- (b) Refractive index at 25°C = 1.4665 to 1.4679;
- (c) Acidity (expressed as % of oleic acid) = 0.5% maximum;
- (d) Peroxide number (expressed as oxygen milli-equivalents per kg of oil) = 10 maximum.

4. The fatty food simulants referred to in the Table are —

- (a) corn oil with standardised specifications;
- (b) sunflower oil, the characteristics of which are —

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

- (i) Iodine value (Wijs) = 120 to 145;
 - (ii) Refractive index at 20°C = 1.474 to 1.476;
 - (iii) Saponification number = 188 to 193;
 - (iv) Relative density at 20°C = 0.918 to 0.925;
 - (v) Unsaponifiable matter = 0.5% to 1.5%;
- (c) a synthetic mixture of triglycerides the composition of which is as set out in the following tables:

Fatty acid distribution

No of C-atoms in fatty acid residue	6	8	10	12	14	16	18	others
GLC area (%)	~1	6-9	8-11	45-52	12-15	8-10	8-12	1

Purity

Content of monoglycerides (enzymatically)	<0.2%
Content of diglycerides (enzymatically)	<2.0%
Unsaponifiable matter	<0.2%
Iodine value (Wijs)	<0.1%
Acid value	<0.1%
Water content (K Fischer)	<0.1%
Melting point	28 ± 2°C

Typical absorption spectrum (thickness of layer: d = 1 cm; Reference: water at 35°C)

Wavelength (nm)	290	310	330	350	370	390	430	470	510
Transmittance (%)	~2	~15	~37	~64	~80	~88	~95	~97	~98
At least 10% light transmittance at 310 nm									

5. Where a fatty food simulant specified in paragraph 4 is used in migration testing and the result of that test shows that a plastic material or article does not comply with any migration limit specified in regulation 9 or the Annexes, verification that the plastic material or article does not comply with the specified migration shall be carried out by testing that material or article using olive oil if such testing is technically feasible, and if such testing is not technically feasible the plastic material or article shall be deemed not to comply with the specified migration limit.

PART 3

Selection of Food Simulants

Testing, reduction factors and definition of food types

1. The testing of plastic materials and articles shall be carried out under the test conditions specified in Part 5 using a simulant or simulants selected in accordance with this Part and taking a new test specimen of the plastic material or article for each simulant used.

2.—(1) Where a test is carried out on a plastic material or article intended to come into contact with more than one food or group of foods and a reduction factor is specified for one or more of those foods or groups of foods which is not equivalent to the reduction factor specified for one or more of the other foods or groups of foods with which the plastic material or article is intended to come into contact—

- (a) the reduction factor specified for each food or group of foods, as appropriate, shall be applied to the test result; and
- (b) the plastic material or article shall be treated as being capable of transferring its constituents to food with which it may come into contact in excess of a migration limit specified in regulation 9 or the Annexes if, following application of those specified reduction factors, one or more of the results show that the material or article does not comply with that specified migration limit.

(2) For the purpose of this paragraph —

- (a) a reduction factor is the figure which follows an “X” and oblique stroke in the group of columns headed “Simulants to be used” in the Table to Part 4;
- (b) a reduction factor is specified for a food or group of foods where, in the Table to Part 4 —
 - (i) the food or group of foods is described in the column headed “Description of food”, and
 - (ii) “X” is placed in a column headed by a specified simulant opposite that food or group of foods followed by an oblique stroke and a reduction factor;
- (c) a reduction factor shall be applied to a test result by dividing the result by that reduction factor.

3. Food types are defined in Table 1 as follows —

Table 1: Food types

<i>Definition</i>	<i>Meaning</i>
Aqueous foods having a pH > 4.5	Foods in relation to which simulant A only is specified in the Table to Part 4
Acidic foods having a pH < 4.5	Foods in relation to which simulant B only is specified in Table to Part 4
Alcoholic foods	Foods in relation to which simulant C only is specified in the Table to Part 4
Fatty foods	Foods in relation to which simulant D only is specified in the Table to Part 4
Dry Foods	Foods in relation to which no simulant is specified in the Table to Part 4

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) [View outstanding changes](#)

Selection of simulants for testing materials and articles intended for contact with all food types

4. The simulants to be used in testing a plastic material or article which is intended for contact with all food types are simulant B, simulant C and simulant D which, at the test conditions specified in Part 5, are considered to be more severe.

Selection of simulants for testing materials and articles which are already in contact with a known food

5. The simulant to be used in testing a plastic material or article which is already in contact with a known food shall be —

(a) where —

(i) the known food is a specific food or is within a specific group of foods described in column 2 of the Table to Part 4 and,

(ii) for the purposes of that Part, a simulant is specified in relation to that specific food or specific group of foods,

the simulant so specified;

(b) where —

(i) the known food is neither a specific food, nor

(ii) within a specific group of foods described in the Table to Part 4 of this Schedule,

the simulant in column 2 of Table 2 opposite the description of food in column 1 of that Table which corresponds most closely to the known food.

Selection of simulants for testing materials and articles which are accompanied by a specific indication

6. The simulant to be used in testing a plastic material or article which, pursuant to Regulation 1935/2004 is accompanied by a specific indication stating any type or types of food described in Table 1 with which it may or may not be used shall be the simulant in column 2 of Table 2 opposite the contact food in column 1 of that Table which corresponds most closely to the type or types of food with which it may be used, as identified by the indication which accompanies the plastic material or article.

7. The simulant to be used in testing a plastic material or article which, pursuant to Regulation 1935/2004, is accompanied by a specific indication, expressed in accordance with paragraph 8, stating any food or group of foods described in the Table to Part 4 with which it may or may not be used shall be—

(a) where the indication states that the plastic material or article may be used with a food or group of foods described in column 2 of the Table to Part 4, the food simulant which, for the purposes of Part 4, is specified in relation to that food or group of foods;

(b) where the indication states that the plastic material or article should not be used with any food or group of foods described in column 2 of the Table to Part 4, a simulant other than one specified, for the purposes of Part 4, in relation to that food or group of foods.

8. A specific indication referred to in paragraph 7 is expressed in accordance with this paragraph if it is expressed—

(a) at a marketing stage other than retail, by using the reference number in column 1 of the Table to Part 4 or the description of food in column 2 of that Table which, in either case, corresponds to the food;

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

- (b) at the retail stage, by using an indication which refers to only a few foods or groups of foods described in the Table to Part 4.

Table 2: Simulants to be selected for testing food contact materials in special cases

<i>Contact foods</i>	<i>Simulant</i>
Only aqueous foods	Simulant A
Only acidic foods	Simulant B
Only alcoholic foods	Simulant C
Only fatty foods	Simulant D
All aqueous and acidic foods	Simulant B
All alcoholic and aqueous foods	Simulant C
All alcoholic and acidic foods	Simulant C and B
All fatty and aqueous foods	Simulants D and A
All fatty and acidic foods	Simulants D and B
All fatty, alcoholic and aqueous foods	Simulants D and C
All fatty, alcoholic and acidic foods	Simulants D, C and B

PART 4

Simulants to be used in relation to a Specific Food or Group of Foods

1. For the purposes of this Schedule a simulant is specified in relation to a specific food or a specific group of foods where “X” is placed in the column headed by that simulant opposite that specific food or specific group of foods in the Table to this Part, and the Table shall be read in conjunction with the notes to it and with paragraphs 2 to 5.

2. For the purposes of this Part —

- (a) a reduction factor is the figure which follows an “X” and oblique stroke in the group of columns headed “Simulants to be used” in the Table to this Part;
- (b) a reduction factor is specified in relation to a specific food or group of foods where, in the Table —
 - (i) the food or group of foods is described in the column headed “Description of food”; and
 - (ii) “X” is placed in a column headed by a specified simulant opposite that food or group of foods followed by an oblique stroke and a reduction factor.

3. Where a reduction factor is specified in the Table in relation to a specific food or a specific group of foods, that reduction factor shall be applied to the result of any migration test using the simulant specified in relation to that food or group of foods by dividing the result of the test by the reduction factor.

4.—(1) Where the letter “a” is shown in brackets after the “X”, only one of the two simulants specified shall be used in the migration test, that is to say —

- (a) if the pH value of the food is higher than 4.5, simulant A shall be used;

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

(b) if the pH value of the foodstuff is 4.5 or less, simulant B shall be used.

(2) Where the letter “b” is shown in brackets after the “X”, the indicated test shall be carried out with ethanol 50% (v/v).

5. Where a food is listed in the Table under both a specific and a general heading, the simulant relating to the specific heading is the simulant which falls to be used for the migration test.

Reference Number	Description of food	Simulants to be used			
		A	B	C	D
01	Beverages				
01.01	Non-alcoholic beverages or alcoholic beverages of an alcoholic strength lower than 5% vol: — Waters, ciders, fruit or vegetable juices of normal strength or concentrated, musts, fruit nectars, lemonades and mineral waters, syrups, bitters, infusions, coffee, tea, liquid chocolate, beers and other	X(a)	X(a)		
01.02	Alcoholic beverages of an alcoholic strength equal to or exceeding 5% vol. — Beverages shown under heading 01.01 but with an alcoholic strength equal to or exceeding 5% vol. — Wines, spirits and liqueurs		X ⁽¹⁾	X ⁽²⁾	
01.03	Miscellaneous: undenatured ethyl alcohol		X ⁽¹⁾	X ⁽¹⁾	
02	Cereals, cereal products, pastry, biscuits, cakes and other bakers’ wares				
02.01	Starches				
02.02	Cereals, unprocessed, puffed, in flakes (including popcorn, cornflakes and the like)				
02.03	Cereal flour and meal				
02.04	Macaroni, spaghetti and similar products				
02.05	Pastry, biscuits, cakes and other bakers’ wares, dry: A With fatty substances on the surface B Other				X/5

(1) Simulant B shall not be used where the pH is more than 4.5.

(2) This test shall be carried out in the case of liquids or beverages of an alcoholic strength exceeding 10% vol. with aqueous solutions of ethanol of a similar strength.

(3) If it can be demonstrated under regulation 13(2) or proved by means of an appropriate test that there is to be no fatty contact with the plastic material or article, simulant D shall not be used.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

Reference Number	Description of food	Simulants to be used			
		A	B	C	D
02.06	Pastry, biscuits, cakes and other bakers' wares, fresh A With fatty substances on the surface B Other	X			X/5
03	Chocolate, sugar and products thereof Confectionery products				
03.01	Chocolate, chocolate-coated products, substitutes and products coated with substitutes				X/5
03.02	Confectionery products: A in solid form — with fatty substances on the surface — Other B in paste form: — with fatty substances on the surface — moist	X			X/5 X/3
03.03	Sugar and sugar products A In solid form B Honey and the like C Molasses and sugar syrups	X X			
04	Fruit, vegetable and products thereof				
04.01	Whole fruit, fresh or chilled				
04.02	Processed fruit: A Dried or dehydrated fruit, whole or in the form of flour or powder B Fruit in the form of chunks, puree or paste C Fruit preserves (jams and similar products – whole fruit or chunks or in the form of flour or powder, preserved in a liquid medium): — i) In an aqueous medium — ii) In an oily medium — iii) In an alcoholic medium > 5% vol	X(a) X(a) X(a)	X(a) X(a) X(a) X ⁽¹⁾		X

- (1) Simulant B shall not be used where the pH is more than 4.5.
- (2) This test shall be carried out in the case of liquids or beverages of an alcoholic strength exceeding 10% vol. with aqueous solutions of ethanol of a similar strength.
- (3) If it can be demonstrated under regulation 13(2) or proved by means of an appropriate test that there is to be no fatty contact with the plastic material or article, simulant D shall not be used.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

Reference Number	Description of food	Simulants to be used			
		A	B	C	D
04.03	Nuts (peanuts, chestnuts, almonds, hazelnuts, walnuts, pine kernels and others) A Shelled, dried B Shelled and roasted C In paste or cream form	X			X/5 ⁽³⁾ X/3 ⁽³⁾
04.04	Whole vegetables, fresh or chilled				
04.05	Processed vegetables: A Dried or dehydrated vegetables whole or in the form of flour or powder B Vegetables, cut, in the form of purees C Preserved vegetables: — i) In an aqueous medium — ii) In an oily medium — iii) In an alcoholic medium (> 5% vol)	X(a) X(a) X(a)	X(a) X(a) X ⁽¹⁾		X X
05	Fats and oils				
05.01	Animal and vegetable fats and oils, whether natural or treated (including cocoa butter, lard, resolidified butter)				X
05.02	Margarine, butter and other fats and oils made from water emulsions in oil				X/2
06	Animal products and eggs				
06.01	Fish: A Fresh, chilled, salted, smoked B In the form of paste	X X			X/3 ⁽³⁾ X/3 ⁽³⁾
06.02	Crustaceans and molluscs (including oysters, mussels, snails) not naturally protected by their shells	X			
06.03	Meat of all zoological species (including poultry and game): A Fresh, chilled, salted, smoked B In the form of paste, creams	X X			X/4 X/4

- (1) Simulant B shall not be used where the pH is more than 4.5.
- (2) This test shall be carried out in the case of liquids or beverages of an alcoholic strength exceeding 10% vol. with aqueous solutions of ethanol of a similar strength.
- (3) If it can be demonstrated under regulation 13(2) or proved by means of an appropriate test that there is to be no fatty contact with the plastic material or article, simulant D shall not be used.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

Reference Number	Description of food	Simulants to be used			
		A	B	C	D
06.04	Processed meat products (ham, salami, bacon and other)	X			X/4
06.05	Preserved and part-preserved meat and fish: A In an aqueous medium B In an oily medium	X(a) X(a)	X(a) X(a)		 X
06.06	Eggs not in shell: A Powdered or dried B Other	 X			
06.07	Egg yolks: A Liquid B Powdered or frozen	 X			
06.08	Dried white of egg				
07	Milk products				
07.01	Milk: A Whole B Partly dried C Skimmed or partly skimmed D Dried				 X(b) X(b) X(b)
07.02	Fermented milk such as yoghurt, buttermilk and such products in association with fruit and fruit products		X		X(b)
07.03	Cream and sour cream		X(a)		X(b)
07.04	Cheeses: A Whole, with non-edible rind B All others	 X(a)	 X(a)		 X/3 ⁽³⁾
07.05	Rennet: A In liquid or viscous form B Powdered or dried	 X(a)	 X(a)		
08	Miscellaneous products				
08.01	Vinegar		X		
08.02	Fried or roasted foods:				

- (1) Simulant B shall not be used where the pH is more than 4.5.
- (2) This test shall be carried out in the case of liquids or beverages of an alcoholic strength exceeding 10% vol. with aqueous solutions of ethanol of a similar strength.
- (3) If it can be demonstrated under regulation 13(2) or proved by means of an appropriate test that there is to be no fatty contact with the plastic material or article, simulant D shall not be used.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

Reference Number	Description of food	Simulants to be used			
		A	B	C	D
	A Fried potatoes, fritters and the like B Of animal origin				X/5 X/4
08.03	Preparations for soups, broths in liquid, solid or powder form (extracts, concentrates); homogenized composite food preparations, prepared dishes: A Powdered or dried — i) With fatty substances on the surface — ii) Other B Liquid or paste: — i) With fatty substances on the surface — ii) Other				X/5 X/3
08.04	Yeasts and raising agents: A In paste form B Dried	X(a)	X(a)		
08.05	Salt				
08.06	Sauces: A Without fatty substances on the surface B Mayonnaise, sauces derived from mayonnaise, salad creams and other oil in water emulsions C Sauce containing oil and water forming two distinct layers	X(a) X(a) X(a)	X(a) X(a) X(a)		X/3 X
08.07	Mustard (except powdered mustard under heading 08.17)	X(a)	X(a)		X/3 ⁽³⁾
08.08	Sandwiches, toasted bread and the like containing any kind of foodstuff: A With fatty substances on the surface B Other				X/5
08.09	Ice-creams	X			
08.10	Dried foods: A With fatty substances on the surface				X/5

- (1) Simulant B shall not be used where the pH is more than 4.5.
- (2) This test shall be carried out in the case of liquids or beverages of an alcoholic strength exceeding 10% vol. with aqueous solutions of ethanol of a similar strength.
- (3) If it can be demonstrated under regulation 13(2) or proved by means of an appropriate test that there is to be no fatty contact with the plastic material or article, simulant D shall not be used.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

Reference Number	Description of food	Simulants to be used			
		A	B	C	D
	B Other				
08.11	Frozen or deep-frozen foods				
08.12	Concentrated extracts of an alcoholic strength equal to or exceeding 5% vol		X ⁽¹⁾	X	
08.13	Cocoa: A Cocoa powder B Cocoa paste				X/5 ⁽³⁾ X/3 ⁽³⁾
08.14	Coffee, whether or not roasted, decaffeinated or soluble, coffee substitutes, granulated or powdered				
08.15	Liquid coffee extracts	X			
08.16	Aromatic herbs and other herbs: Camomile, mallow, mint, tea, lime blossom and others				
08.17	Spices and seasonings in the natural state: Cinnamon, cloves, powdered mustard, pepper, vanilla, saffron and other				

- (1) Simulant B shall not be used where the pH is more than 4.5.
- (2) This test shall be carried out in the case of liquids or beverages of an alcoholic strength exceeding 10% vol. with aqueous solutions of ethanol of a similar strength.
- (3) If it can be demonstrated under regulation 13(2) or proved by means of an appropriate test that there is to be no fatty contact with the plastic material or article, simulant D shall not be used.

PART 5

Migration Test Conditions (Times and Temperatures)

General criteria

1. Subject to paragraphs 2, 4, 6 and 7 and to paragraph 4.4 of Chapter II of the Annex to Directive 82/711, when carrying out migration tests the time and temperature used shall be the time and temperature selected from column 2 of the Table to this Part which correspond to the worst foreseeable conditions of contact specified in column 1 of that Table for the plastic material or article being tested and to any labelling information on maximum temperature for use.

2. Where the plastic material or article being tested is intended for a food contact application covered by a combination of two or more times and temperatures specified in column 2 of the Table to this Part, the migration test shall be carried out by subjecting the test specimen successively to all the applicable worst foreseeable conditions appropriate to the sample, using the same portion of food simulant.

3. For the purposes of this Part the worst foreseeable conditions of contact are those which are recognised to be the most severe on the basis of scientific evidence.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

Volatile migrants

4. When carrying out a test of the specific migration of volatile substances any test using a simulant shall be performed in a manner that recognises the loss of volatile migrants which may occur in the worst foreseeable conditions of use.

Special cases

5. When carrying out a migration test of a plastic material or article that is intended for use in a microwave oven, if the appropriate time and temperature is selected from the Table to this Part, either a conventional oven or a microwave oven may be used.

6. Where the carrying out of a migration test under contact conditions specified in the Table to this Part causes any physical or other change in the test specimen that does not occur under the worst foreseeable conditions of use of the plastic material or article being tested, the migration test shall be carried out in the worst foreseeable conditions of use in which such physical or other change does not occur.

7. Where, in actual use, the plastic material or article being tested is intended to be used for periods of less than 15 minutes at any temperature of not less than 70°C and not more than 100°C and such use is indicated by appropriate labelling or instructions, no test other than for 2 hours at 70°C shall be carried out on the plastic material or article unless the plastic material or article is also intended to be used for storage at room temperature, in which case no test other than for 10 days test at 40°C shall be carried out.

8. The Table to this Part shall be read with the notes to it.

<i>Conditions of contact in worst foreseeable use</i>	<i>Test conditions</i>
Contact time:	Test time:
less than or equal to 5 minutes	(1)
>5 minutes but less than or equal to 0.5 hours	0.5 hours
>0.5 hours but less than or equal to 1 hour	1 hour
>1 hour but less than or equal to 2 hours	2 hours
>2 hours but less than or equal to 4 hours	4 hours
>4 hours but less than or equal to 24 hours	24 hours
>24 hours	10 days
Contact temperature:	Test temperature:
less than or equal to 5°C	5°C
>5°C but less than or equal to 20°C	20°C
>20°C but less than or equal to 40°C	40°C
>40°C but less than or equal to 70°C	70°C
>70°C but less than or equal to 100°C	100°C or reflux temperature

(1) The period of time which represents the worst foreseeable conditions of contact.

(2) This temperature shall be used only for simulant D. For simulant A, B or C the test may be replaced by a test at 100°C or at reflux temperature for a duration of four times the time selected in accordance with paragraph 1.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

<i>Conditions of contact in worst foreseeable use</i>	<i>Test conditions</i>
>100°C but less than or equal to 121°C	121°C ⁽²⁾
>121°C but less than or equal to 130°C	130°C ⁽²⁾
>130°C but less than 150°C	150°C ⁽²⁾
>150°C	175°C ⁽²⁾

- (1) The period of time which represents the worst foreseeable conditions of contact.
- (2) This temperature shall be used only for simulant D. For simulant A, B or C the test may be replaced by a test at 100°C or at reflux temperature for a duration of four times the time selected in accordance with paragraph 1.

PART 6

Substitute Fat Test for Overall and Specific Migration

- Subject to paragraphs 2, 4 and 5, all the test media specified in the Table to this Part shall be used in the substitute fat test for overall or specific migration under the test conditions corresponding to the test conditions for simulant D.
- Test conditions other than those specified in the Table to this Part may be used in the substitute fat test if the assumptions underlying the test conditions specified in that Table and, where the plastic material or article being tested is a polymer, the existing experience of that type of polymer are taken into account.
- For each test—
 - a new test specimen shall be used;
 - the rules prescribed for simulant D in Parts 3, 4 and 5 shall be applied for each test medium;
 - subject to paragraph 4, compliance with a migration limit shall be determined by selecting the highest value using all the test methods.
- Where carrying out a migration test causes any physical or other change in the test specimen which does not occur under the worst foreseeable conditions of use of the plastic material or article the result of that test shall not be used to ascertain compliance with a migration limit.
- Any test conditions in the Table to this Part which are generally recognised on the basis of scientific evidence as not being appropriate for the material or article to be tested shall not be used.
- The Table to this Part shall be read with the notes to it.

Conventional conditions for substitute tests

<i>Test conditions with simulant D</i>	<i>Test conditions with isooctane</i>	<i>Test conditions with ethanol 95%</i>	<i>Test conditions with MPPO⁽¹⁾</i>
10 days at 5°C	0.5 days at 5°C	10 days at 5°C	
10 days at 20°C	1 day at 20°C	10 days at 20°C	

- (1) MPPO = Modified polyphenylene oxide
- (2) The volatile test media are used up to a maximum temperature of 60°C. A precondition of using these tests is that the material or article will withstand the test conditions that would otherwise be used with simulant D. Immerse a test specimen in olive oil under the appropriate conditions. If the physical properties are changed (eg melting, deformation) then the material is considered unsuitable for use at that temperature. If the physical properties are not changed then proceed with the substitute tests using new specimens.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

<i>Test conditions with simulant D</i>	<i>Test conditions with isooctane</i>	<i>Test conditions with ethanol 95%</i>	<i>Test conditions with MPPO⁽¹⁾</i>
10 days at 40°C	2 days at 20°C	10 days at 40°C	
2 hours at 70°C	0.5 hours at 40°C	2 hours at 60°C	
0.5 hours at 100°C	0.5 hours at 60°C ⁽²⁾	2.5 hours at 60°C	0.5 hours at 100°C
1 hour at 100°C	1 hour at 60°C ⁽²⁾	3 hours at 60°C ⁽²⁾	1 hour at 100°C
2 hours at 100°C	1.5 hours at 60°C ⁽²⁾	3.5 hours at 60°C ⁽²⁾	2 hours at 100°C
0.5 hours at 121°C	1.5 hours at 60°C ⁽²⁾	3.5 hours at 60°C ⁽²⁾	0.5 hours at 121°C
1 hour at 121°C	2 hours at 60°C ⁽²⁾	4 hours at 60°C ⁽²⁾	1 hour at 121°C
2 hours at 121°C	2.5 hours at 60°C ⁽²⁾	4.5 hours at 60°C ⁽²⁾	2 hours at 121°C
0.5 hours at 130°C	2 hours at 60°C ⁽²⁾	4 hours at 60°C ⁽²⁾	0.5 hours at 130°C
1 hour at 130°C	2.5 hours at 60°C ⁽²⁾	4.5 hours at 60°C ⁽²⁾	1 hour at 130°C
2 hours at 150°C	3 hours at 60°C ⁽²⁾	5 hours at 60°C ⁽²⁾	2 hours at 150°C
2 hours at 175°C	4 hours at 60°C ⁽²⁾	6 hours at 60°C ⁽²⁾	2 hours at 175°C

(1) MPPO = Modified polyphenylene oxide

(2) The volatile test media are used up to a maximum temperature of 60°C. A precondition of using these tests is that the material or article will withstand the test conditions that would otherwise be used with simulant D. Immerse a test specimen in olive oil under the appropriate conditions. If the physical properties are changed (eg melting, deformation) then the material is considered unsuitable for use at that temperature. If the physical properties are not changed then proceed with the substitute tests using new specimens.

PART 7

Alternative Fat Tests for Overall and Specific Migration

1. Subject to paragraph 2 the conditions which must be fulfilled to allow the result of either test specified in paragraph 3 to be used as an alternative to the result of a migration test carried out under Part 3 are that—

- (a) the result obtained in a “comparison test” shows that the values are equal to or greater than those obtained in the test with simulant D; and
- (b) the migration occurring in either test specified in paragraph 3 does not, after application of the appropriate reduction factor, exceed the appropriate migration limit.

2. The condition in sub-paragraph (a) of paragraph 1 does not have to be fulfilled if it can be shown on the basis of the result of scientific experiment that the values obtained in either of the tests specified in paragraph 3 are equal to or greater than those obtained in any of the migration tests specified in Part 3.

3. The migration tests referred to in paragraphs 2 and 3 are —

- (a) a test carried out using volatile media including isooctane, ethanol 95%, other volatile solvents or a mixture of solvents at such contact conditions as would result in values equal to or greater than those obtained in a test using simulant D;

Changes to legislation: There are outstanding changes not yet made by the [legislation.gov.uk](https://www.legislation.gov.uk) editorial team to *The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008*. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) [View outstanding changes](#)

- (b) other tests using media having a very strong extraction power under very severe test conditions where, on the basis of scientific evidence, it is generally recognised that the results using these tests are equal to or higher than those obtained in a test using simulant D.

SCHEDULE 4

Regulation 14

Information to be contained in a declaration of compliance

1. The name and address of the business operator which manufactures or imports the plastic materials or articles or the substances intended for the manufacture of those materials or articles.
2. The identity of the materials, articles or substances intended for their manufacture.
3. The date of the declaration.
4. Confirmation that the plastic materials or articles meet the relevant requirements laid down in the Directive and in Regulation 1935/2004.
5. Adequate information relating to the substances used for which restrictions or specifications are in place under the Directive to allow downstream business operators to ensure compliance with them.
6. Adequate information relating to the substances which are subject to a restriction in food, obtained by experimental data or theoretical calculation about the level of their specific migration and, where appropriate, purity criteria in accordance with the purity Directives to enable the user of the plastic materials or articles to comply with the relevant Community provisions or, in their absence, with national provisions applicable to food.
7. Specifications on the use of the plastic material or article, such as —
 - (a) the types of food intended to be in contact with it;
 - (b) the time and temperature of treatment and storage in contact with the food;
 - (c) the ratio of food contact surface area to volume used to establish the compliance of the plastic material or article.
8. Confirmation, when a plastic functional barrier is used in a plastic multi-layer, that the plastic material or article complies with the requirements of paragraphs 2 to 4 of Article 7a of the Directive.”

EXPLANATORY NOTE

(This note is not part of the Regulations)

These Regulations provide for the execution and enforcement in Northern Ireland of [Commission Regulation \(EC\) No. 597/2008](#) amending [Commission Regulation \(EC\) No. 372/2007](#) laying down transitional migration limits for plasticisers in gaskets in lids intended to come into contact with foods, (“the new Commission Regulation”). The new Commission Regulation extends the relevant deadline for such materials and articles to 30th April 2009.

Changes to legislation: *There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes*

These Regulations provide for the execution and enforcement of the new Commission Regulation by amending regulation 21(3) of the Plastic Materials and Articles in Contact with Food Regulations (Northern Ireland) 2008 (“the principal Regulations”) (*regulation 5*), and omitting regulation 27(c) of those Regulations (*regulation 6*).

These Regulations also correct four errors in the principal Regulations (*regulations 3, 4, 5 and 7*), and make a consequential amendment (*regulation 8*).

These Regulations also make an amendment to the Food Safety (Sampling and Qualifications) Regulations (Northern Ireland) 1991, required due to the revocation of the Plastic Materials and Articles in Contact with Food (No.2) Regulations (Northern Ireland) 2006 by the principal Regulations (*regulation 9*).

Changes to legislation:

There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (Amendment) Regulations (Northern Ireland) 2008. Any changes that have already been made by the team appear in the content and are referenced with annotations.

[View outstanding changes](#)

Changes and effects yet to be applied to :

- [reg. 2-7](#) revoked by [S.R. 2009/56 reg. 26\(b\)](#)