

SCHEDULE 5

THE MATCH TEST

PART I

1. All braids and other trimmings shall be removed from material upon which a test is to be conducted.

2. Any covering fabric which has been treated with a fire-retardant chemical to reduce the ignitability of the upholstery shall, before it is conditioned in accordance with clause 7.1 of B.S. 5852: Part 1 be subjected to the water-soaking procedure set out in clauses 4.2 to 4.5 of B.S. 5651, save that for the second subclause of clause 4.5 there shall be substituted the following:

“After 30 minutes, remove the specimen, rinse in water (4.2.1) using a liquor ratio of 1:20 for 2 minutes, and then dry the specimen by any method suitable for the fabric type.”

3. The test shall be carried out in accordance with those provisions of BS 5852: Part 1 which relate to butane flame ignition source 1. The filling material for this test shall be non-fire retardant polyurethane foam corresponding to the specification set out in BS 3379 Type B Hardness grade 130 and of a density of 20–22 kg per m³.

4. The criteria of failure shall be those specified in clause 4 of BS 5852: Part 1.